

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C07F 5/00, C23C 16/18, C10L 1/14	A1	(11) International Publication Number: WO 94/17078 (43) International Publication Date: 4 August 1994 (04.08.94)
(21) International Application Number: PCT/GB94/00120 (22) International Filing Date: 21 January 1994 (21.01.94) (30) Priority Data: 9301242.5 22 January 1993 (22.01.93) GB (71)(72) Applicants and Inventors: LEEDHAM, Timothy, John [GB/GB]; Crossing Keeper Cottage, Fen Road, Milton, Cambs CB4 6AF (GB). DRAKE, Simon, Robert [GB/GB]; 164 Florence Road, Wimbledon, London SW19 8TN (GB). (74) Agents: COLLIER, Jeremy, Austin, Grey et al.; J.A. Kemp & Co., 14 South Square, Gray's Inn, London WC1R 5LX (GB).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, LV, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: RARE EARTH COMPOUNDS AND THEIR PREPARATION (57) Abstract The invention provides rare earth compounds of formula $[(ML_3)_x A]_y$ where M is one or more of the rare earth metals and yttrium, L is a beta-diketone type ligand, A is a polyether or polyamine, and x and y are each 1 or 2. These compounds are precursors for chemical vapour deposition (CVD) of oxide layers in applications such as superconductors, piezoelectrics, microwaves, fuel cells, radiation detectors, optoelectronics, and catalysts. They are air and moisture stable, low melting, vacuum volatile at low temperatures leaving minimum residue and give good quality metal oxide deposits uncontaminated by fluorine. These compounds also have excellent solubility in a wide range of organic solvents, and are potentially useful as oil lubricant additives and in fuels.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

RARE EARTH COMPOUNDS AND THEIR PREPARATION

This invention relates to rare earth compounds and their preparation. The term "rare earth" as used herein means a lanthanide element plus yttrium.

5

BACKGROUND

There is a considerable need for molecular precursors for Chemical Vapour Deposition (CVD) or Sol-gel processes to fabricate Lanthanide based materials. These are of potential importance as precursors of multimetallic oxides. For such
10 precursors to find ready application, they should be stable in the gas phase and have good mass transport properties, thereby allowing the formation of a thin or thick film of either the metal or metal oxide to be deposited onto the desired substrate.

15 A major potential use of such precursors is in the synthesis of electroceramics, e.g. high temperature superconductor ceramic thin or thick films for use in electronic devices such as $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$; see P. P. Edwards et. al. Chemistry Britain, 1987, 23-26., $\text{Pb}_2\text{Sr}_2\text{LnCu}_3\text{O}_{8-x}$; M. O'Keefe
20 and S. Hansen, J. Am. Chem. Soc. 1988, 110 1506, R.J. Cava et. al. Nature, (London), 1988, 336, 211-214; $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$; Bednorz and Muller, Z. Phys. B. Cond. Matter, 1986, 64, 189-195; piezoelectrics such as LaCuO_2 ; Müller-Buschbaum, Angew. Chem. 1989, 28, 1472-74 and phosphors and fuel cells.

- 2 -

Multimetallic oxide based ceramics are conventionally made by "heat and bake" technology; see D. Segal, Chemical Synthesis of Advanced Ceramic Materials, Cambridge University Press, Cambridge, 1991. This approach relies upon the intimate mixing of metal-oxygen based materials (e.g. metal carbonates, nitrates or hydroxides) by the use of techniques such as ball-milling, fusion processes, and uniaxial or hot isostatic pressing. Although these processes are attractive owing to their inherent simplicity and low cost, there are several inherent disadvantages. These are high temperature processing and post-annealing under a flow of oxygen gas, which ensures that any meta-stable phases cannot be accessed by this approach. There is also the added difficulty of phase inhomogeneity, e.g. tetragonal and orthorhombic forms of $\text{YCu}_2\text{Ba}_3\text{O}_{7-x}$ present in the same material, and also the presence of ionic impurities (e.g. BaCO_3) frequently found at the grain boundaries.

An alternative strategy involves the use of metal alkoxides or β -diketonates; see Mehrotra *et. al.* Chem. Rev. 1991, 91, 1287-1302. These compounds are readily obtained as crystalline solids of known stoichiometry, high purity, good solubility in organic solvents, and long term stability in an inert atmosphere, and are sufficiently reactive that most reactions occur at or near room temperature. By using such materials fine control of molecular stoichiometry is

- 3 -

possible and access to previously unobtainable metastable phases is achievable. These materials find extensive use in either sol-gel or chemical vapour deposition (CVD) processes, which involve the formation of either thick films (sol-gel spun coating) or ultrathin films (20 Å or less) for optical or microelectronic applications by CVD.

However, conventional lanthanide precursors for metal oxide films have several drawbacks, notably in the high residue left in commercial evaporators/bubblers for CVD and poor stability in the atmosphere. The use of fluorinated precursors results in the formation of LnF_3 , which has to be removed with either superheated water vapour or air at elevated temperature to yield the required oxide based film. Therefore, to produce epitaxial or high quality films it is important to avoid the use of fluoride based compounds, even though such complexes have excellent vapour pressure and mass transport properties. Thus, as stated above, a precursor is required that vapourises without any decomposition and remains intact in the vapour phase for considerable time periods, i.e. for at least the length of time of the CVD process.

Lanthanide metal alkoxides and β -diketonates are well known materials; see K.S. Mazdiasni *et al* Inorg. Chem., 1966, 3, 342-347; K. S. Mazdiasni *et al* J. Less-Common Met., 1973, 30, 105-112, and R. C. Mehrotra *et al*, Metal Beta-diketones", Academic Press, London, 1978. A considerable

- 4 -

degree of diversity has been previously found in their chemistry, notably with added Lewis bases; see T. Moeller et.al. Gmelin Handbook of Inorganic Chemistry, Sc, Y, La-Lu Rare Earth Elements Part D3, 8th Edn, Springer, Berlin, 1981.

- 5 The most commonly used strategies for preparing volatile metal precursors are the use of bulky or alternatively fluorinated ligands that encapsulate the metal ions, and thus create discrete molecular species. This phenomenon occurs due to reduced intermolecular associations between metal
- 10 centres, and therefore changes the orientation of the packing in the solid or liquid states; this in turn gives rise to enhanced thermal and mass transport properties. This approach has been recently adopted for the lanthanide complexes; see W. J. Evans et al., Inorg. Chem., 1989, 28, 4308-4314; M. J. McGearry et al., Inorg. Chem., 1991, 30, 1723-1724; E. H. Barash et al., Inorg. Chem., 1993, 32, 497-502; and R. E. Sievers, Science, 1978, 201, 217-223.

Because of their large ionic radii and coordination numbers the lanthanides are difficult to coordinatively

20 saturate to yield monomeric complexes. Bulky ligands are limited in their ability to coordinatively saturate these highly Lewis acidic metals, i.e. poly-functionalised ligands have been extensively used, $[Y(OCH_2CH_2OMe)_3]_{10}$; see O. Poncolet et al. J. Chem. Soc., Chem. Commun., 1989, 1846-47; and

25 $[Y_3(OCH_2CH_2OMe)_5(acac)_4]$; see O. Poncolet et al. Inorg. Chem.,

- 5 -

1990, 29, 2885-2890. There are also other lanthanide complexes which contain simple ligands (e.g. $\text{Pr}^{\text{t}}\text{O}$ and $\text{Bu}^{\text{t}}\text{O}$), which are not sufficiently electron rich to supply the electronic and steric requirements of these metals; see D.C.

5 Bradley et al., Polyhedron, 1990, 9, 719-725 and 10, 1049-1056. This can lead to highly associated or indeed polymeric complexes, where the ligand is MeO^{\cdot} or EtO^{\cdot} . To date, there has been little success at controlling the degree of oligomerisation of lanthanide molecular precursors.

10 There are a number of synthetic strategies which may be employed to prepare complexes. The most common route utilizes metathesis. A modification of this, especially where the pK_{a} of the beta-diketone is too low (e.g. acac-H), is to use a water-ammonia mixture to drive the reaction to
15 completion, e.g. see $[\text{Ln}(\text{acac})_3(\text{H}_2\text{O})]$, K. J. Eisentraut et al., J. Am. Chem. Soc., 1965, 87, 5254-5259; and G. S. Hammond et al., Inorg.Chem., 1963, 2, 73-75. See also T. Moeller et al. Gmelin Handbook of Inorganic Chemistry, Sc, Y, La-Lu Rare Earth Elements Part D3, 8th Edn, Springer, Berlin, 1981.

20 These known precursor syntheses show limited systematic control of aggregate size and give poorly characterised materials having poor moisture and thermal stability, and a short shelf life. It is therefore highly desirable to synthesise thermally stable and highly soluble materials which
25 are suitable for either CVD or Sol-gel applications.

- 6 -

Compounds for this purpose must satisfy the following physical and chemical criteria :


- defined identity and purity.
- air and moisture stability for ease of handling.
- 5 - low melting point for use in conventional CVD bubbler source chambers.
- good solubility in a wide range of organic solvents.
- significant volatility at low temperature.
- clean pyrolysis at substrate temperatures.
- 10 - give deposited layers free of unwanted impurities.

The present invention provides compounds meeting at least some of these criteria.

The compounds of the invention can be used as precursors for deposition of oxide layers by the chemical vapour
15 deposition (CVD) technique. Rare earth oxides are employed alone or in conjunction with other metal oxides as ceramic or glass layers in a range of advanced materials such as superconductors, piezoelectrics, fuel cells, optoelectronics, radiation detectors, catalysts and to provide thermal and
20 abrasion resistance. The compounds can be used in making devices for use in information technology, medical instrumentation and energy conservation.

The compounds of the invention are the rare earth compounds of formula:

25



- 7 -

where M represents one or more metals chosen from the rare earth metals and yttrium, L is a bidentate ligand, A is a polyether, polyamine or polyether-amine, and x and y are each 1 or 2 but are not both 2. They may be regarded as monomers of formula ML_xA or bridged dimers of formula $(ML_x)_2A$ or $(ML_xA)_2$.

The bidentate ligand L may be a β -diketonate anion containing a group of formula:



derived, more especially, from a compound of formula:



where R^i , R^{ii} , R^{iii} , R^{iv} and R^v are each hydrogen, alkyl of 1 to 6 carbon atoms optionally substituted by fluorine or phenyl, or fluorine, and R^v may also be alkyloxy of 1 to 6 carbon atoms optionally substituted by fluorine, amino, alkylamino, or dialkylamino in which each alkyl has 1 to 6 carbon atoms optionally substituted by fluorine.

Preferably the ligand L is derived from a β -diketone, especially from one or more of acetylacetone, tetramethylheptanedione, trifluoroacetylacetone, hexafluoroacetylacetone, and 1,5-diphenylpentanedione.


The polyether, polyamine or polyether-amine A may be represented by the formula:




- 8 -

where each of R^i , R^{ii} , R^{iii} , R^{iv} , R^{v} and R^{vi} is hydrogen or alkyl of 1 to 6 carbon atoms, Y is -O-, -NR^{vii} (where R^{vii} is hydrogen or alkyl of 1 to 6 carbon atoms), or a mixture thereof, and n is 1 to 10.

5 Preferred polyethers may be represented by the formula:



wherein R^1 , R^2 and R^3 are each hydrogen or alkyl of 1 to 4
10 carbon atoms and n is 1 to 10, and preferred polyamines by the formula:



15 wherein R^1 , R^2 and R^3 and n are as hereinbefore defined.

Especially preferred polyethers are those wherein R^1 and R^2 are each alkyl of 1 to 4 carbon atoms, R^3 is hydrogen, and n is an integer from 1 to 7, more particularly monoglyme, diglyme, triglyme, tetraglyme, and/or heptaglyme.

20 Especially preferred polyamines are those wherein R^1 and R^2 are each alkyl of 1 to 4 carbon atoms, R^3 is hydrogen, and n is an integer from 1 to 3, more particularly tmeda, pmdeta, and/or hmteta.

When A is derived from monoglyme, tetraglyme, tmeda, or
25 pmedta, the monomeric structure is generally formed, i.e. ML_3A . When A is triglyme or heptaglyme a bridged dimeric compound is usually obtained, i.e. $(ML_3)_2A$, and with diglyme,

- 9 -

a dimeric structure having two bridging diglyme molecules can be obtained, i.e. $(ML_2A)_2$.

Type I structure $x=1, y=1$

5 An example of this type of monomeric structure is shown by $[La(thd)_3(tetraglyme)]$. The lanthanum atom binds to all three bidentate thd beta-diketone ligands and to only three of the five possible oxygen atoms of the tetraglyme ligand. Thus the lanthanum atom prefers to adopt a nine-coordinate
10 rather than a possible eleven-coordinate site. A square anti-prismatic geometry is observed for this complex, with the ninth coordinating oxygen atom [O(5)] capping one of the square faces. In this complex the coordinated portion of the glyme has one short La-O bond, 2.706(7) Å [O(2)], and two
15 long La-O bonds, 2.781(6) Å [O(5)] and 2.751(7) Å [O(8)]. The most noticeable and clearly unusual feature of this complex is the presence of the uncoordinated portion of the tetraglyme chain C(9)-C(15) which, with the exception of the terminal methoxy bond, is approximately planar. A study of a
20 space-filling model of this complex indicates that the coordination of an additional glyme oxygen centre is not favourable because of the presence of the three tightly held thd beta-diketone ligands and with three of the five available glyme oxygen atoms saturating the lanathanum metal
25 centre.

- 10 -

Type II structure x=2, y=1

An example of this type of structure is shown by
[Eu(thd)₃]₂(triglyme) which consists of two Eu(thd)₃
moieties linked together by a triglyme ligand involving a
5 unique bonding orientation. Both metal atoms are eight
coordinate with the overall coordination polyhedron being
distorted square antiprismatic. One of the most interesting
features of this complex is the observation that the
triglyme can act as both a chelate and also as a bridging
10 ligand via the central ethylene bridge [C(37)-C(38)]. This
structure allows the utilisation of all four potential
binding sites of the glyme ligand.

The coordination numbers of the metals in these
complexes are eight or nine which is believed to be the
15 principal reason for the advantageous chemical and physical
properties of the compounds (see Table 1 below). Thermal
behaviour has been studied by thermogravimetric analysis and
clearly reveals that these materials volatilize into the
gaseous phase intact, and the first derivative peak shows
20 essentially 96±2 % sublimation for these compounds. The
related melting behaviour has been examined by the use of
differential scanning calorimetry which has demonstrated a
marked reduction in melting point from 200-250°C to 60 - 130°C
on the addition of the multidentate Lewis base ligand.

- 11 -

The compounds of the invention have an advantageously low molecular weight in relation to the amount of rare earth metal or yttrium present. Thus the average molecular weight per metal atom is usual below 2000 and preferably below 1500, and in especially advantageous cases can be below 1000. Alternatively expressed, the metal content may be at least 10%, and preferably at least 15% by weight.

The following Table gives exemplary physical properties of some compounds of the invention.

TABLE 1

Compound	m.p. /°C	evaporation temp. °C/ 10 ⁻² mm Hg.	T _{50%} /°C	residue %	pyrolysis temp. °C
[La(thd) ₃ (tetraglyme)]*	59.9	110	287	3.2	312
[Eu(thd) ₃] ₂ (triglyme)	128.2	115	258	3.7	287
[Tb(thd) ₃] ₂ (triglyme)	115.5	120	242	4.5	330
[Y(thd) ₃] ₂ (triglyme)	95.4	100	223	2.6	255
[Pr(thd) ₃ (triglyme)]	122	140	248	2.3	385
[EuY(thd) ₆](triglyme)	113.8	105	246	5.1	272
[Tb(thd) ₃ (diglyme)] ₂	64.3	110	257	2.2	288
[Y(thd) ₃] ₂ (hmteta)	123.1	120	251	1.9	282
[LaTm(thd) ₆](triglyme)	55.9	115	246	4.9	286

a. This complex is the only material observed to lose its polydentate ligand in the vapour phase to yield [La₂(thd)₆] at ca. 180°C.

The compounds of the invention have excellent solubility in a wide range of organic solvents, e.g. aliphatic solvents, such as n-pentane, hexane, and heptane; aromatic solvents such as benzene, toluene and xylene and coordinating

- 12 -

solvents, e.g. diethylether, tetrahydrofuran, di-n-butylether, dimethylsulphoxide, acetonitrile, pyridine, and chloroform. Indeed, the outstanding solubility shown by the majority of the new compounds ensures that they do not
5 crystallise out of organic solvents. If desired in a crystalline form, then all the organic solvent must be removed, and the compound is crystallised from the oily material remaining.

The excellent solubility of the new compounds in organic
10 solvents makes them suitable for use as additives in lubricants and fuels, including fuels for internal combustion engines and, more especially, hydrocarbon fuels for compression ignition (diesel) engines, for which purpose they may be used typically in a concentration from 10 to 500 ppm,
15 preferably 50 to 200 ppm, by weight calculated as the rare earth metal.

The compounds stated in the prior art to have formulae such as "Ln(thd)₃," where Ln is any rare earth metal or yttrium, actually contain coordinated water or other adducted
20 ligands. Unadducted molecules are oligomers with melting points in the range 200-260°C with evaporation commencing at a slightly higher temperature. Our X-ray studies have shown that these compounds are dimeric complexes, e.g. [Gd₂(thd)₆], with two bridging thd ligands. Unless strictly anhydrous
25 conditions are maintained during preparation they are heavily contaminated with hydrated species which behave unpredictably because of intramolecular hydrolysis when the compounds are heated to their vacuum evaporation points. In general the

- 13 -

rate of evaporation of the prior art compounds declines with time and source chambers become clogged with residue.

These complexes have infrared absorption bands at 1609 ± 5 , 1586 ± 5 and 1540 ± 5 cm^{-1} , assigned to $\nu(\text{C} \equiv \text{O})$ stretching modes and bands at 1575 ± 2 and 1500 ± 5 cm^{-1} assigned to the $\nu(\text{C} \equiv \text{C})$ stretching modes. In the compounds of the invention the glyme ligand $\nu(\text{C} \equiv \text{O})$ bands were observed in the region 1130 ± 10 cm^{-1} , a shift of ca. 50 cm^{-1} compared with the prior art compounds containing no glyme ligand, indicative of strong
10 M-O bonding.

A reason for the oligomerisation and hydration of the prior art compounds is the lack of controlled saturation of the coordination sphere of the metal ion. The compounds of the invention have linear polyether molecules whose oxygen
15 atoms act as Lewis base donors to saturate the Lanthanide metal ion coordination sphere. The outermost architecture of the adducted molecule comprises hydrocarbon groups whose neighbour interactions are weak Van der Waals attractions. Consequently the molecules of this invention exhibit little
20 tendency to associate, and have melting and evaporation points 80 - 150°C below those of the prior art compounds. Moreover, they do not pick up water upon air exposure.


Additionally, the thermal stability of the compounds of the invention in the vapour phase assists deposition by
25 providing an activated species prior to the final step of

- 14 -

pyrolysis to the metal oxide. This is another advantage of the compounds of the invention, see Figures 9-15. The majority of the complexes studied exhibit a sharp reversible melting point in their DSC spectra. The TGA curve shapes for
5 these compounds reveal the presence of a single isothermal step, and near complete vapourisation of these materials by ca. 300°C.

The absence of water in the compounds of the invention is of especial importance. Anhydrous synthesis route I below
10 employs either metal amide or alkoxide starting materials dissolved in hydrocarbon solvent and gives excellent yields. However, these materials are expensive, and routes II or III below give almost as good yields starting from cheaper hydrated salts dissolved, e.g., in methanol. The presence of
15 a small excess of the polyether or amine is apparently sufficient to expel adducted water from the metal coordination sphere.

According to a feature of the invention, the new compounds are made by reacting a rare earth compound of
20 formula:




where M represents one or more metals chosen from the rare earth metals and yttrium, R^4 is alkyl of 1 to 4 carbon atoms or trimethylsilyl, and R^5 is alkyl of 1 to 4 carbon atoms
25 optionally substituted by alkoxy of 1 to 4 carbon atoms with


- 15 -

a bidentate ligand LH and a polyether, polyamine or polyether amine. The reaction may, more particularly, be carried out in a hydrocarbon solvent.

The reaction may be represented:



Where R = Et, Prⁱ or SiMe₃ are the preferred ligands, or




Where R = Prⁱ or Bu^t are the preferred ligands, but may also be, e.g. Me, Et, Prⁿ, or MeOCH₂CH₂-.

10 According to another feature of the invention, the new compounds are made by reacting a rare earth compound of formula: MZ₃(H₂O)₆ where M represents one or more metals chosen from the rare earth metals and yttrium and Z represents an anion with an alkali metal derivative of the

15 bidentate ligand LH and a polyether, polyamine, or polyether-amine A. The reaction may be carried out in an alcohol solvent using a halide, carboxylate, sulphate or nitrate of the rare earth metal.

The reaction may be represented:



where M, L, A, x and y are as defined above and Z = halide, carboxylate, nitrate, or sulphate.

According to yet another feature of the invention, the new compounds are made by reacting a rare earth oxide,

25 hydroxide or carbonate with the bidentate ligand LH and a

- 16 -

polyether, polyamine or polyether-amine A. The reaction may be carried out in an organic, e.g. hydrocarbon, or aqueous solvent. It may be represented:



5 where M, L, A, x and y are as defined above.

In the compounds of the invention the metal centres are coordinatively saturated with the combined use of both a chelating type of Lewis base ligand, i.e. a glyme or amine, and a chelating bidentate group, e.g. a diketone. This
 10 presumably gives rise to the exceptional stability in the atmosphere of the new compounds, since the chelating ligands are less readily hydrolysed than monodentate ligands. Secondly, the use of multidentate ligands reduces the possibility of interactions between monomeric units. Third,
 15 the use of a preformed metal beta-diketonate (whether anhydrous or as a hydrate) leads to water free products. Thus anhydrous metal diketone derivatives can be prepared by a low cost route, e.g. by the use of simple hydrated complexes prepared via metathesis in alcohol/aqueous media.
 20 The observation that water can be removed from the hydrated starting materials is important, and only one equivalent of glyme ligand is needed and not an excess.

The compounds show a further novel property in several cases, e.g. $[La(thd)_3(tetraglyme)]$ (see Figure 1),
 25 $[Gd(thd)_3]_2(tetraglyme)$ (see Figure 7), $[Y(thd)_3]_2(hmteta)$ (see

- 17 -

Figure 3), and $[\text{Gd}(\text{thd})_3]_2(\text{heptaglyme})$ (see Figure 6). In these complexes a portion of the multidentate ether or amine chain is not coordinated to the lanthanide metal centre and may be used to react with an incoming metal complex (e.g. a transition metal or lanthanide) to synthesise previously inaccessible metal combinations, e.g. La-Cu, La-Cu₂, La-Mn, Y-Zr, or Gd-Ce.

The following abbreviations are used herein:

10	thd	tetramethylheptanedionate	$\text{Me}_3\text{CCOCHCOCMe}_3$
	acac	acetylacetonate	MeCOCHCOCMe
	tfa	trifluoroacetylacetonate	$\text{F}_3\text{CCOCHCOCMe}$
15	hfa	hexafluoroacetylacetonate	$\text{F}_3\text{CCOCHCOCF}_3$
	dpp	1,5-diphenylpentanedionate	$\text{PhCH}_2\text{COCHCOCPh}$
20	monoglyme (or dme)	monoethyleneglycol dimethyl ether	$\text{Me}(\text{OCH}_2\text{CH}_2)\text{OMe}$
	diglyme	diethyleneglycol dimethyl ether	$\text{Me}(\text{OCH}_2\text{CH}_2)_2\text{OMe}$
25	triglyme	triethyleneglycol dimethyl ether	$\text{Me}(\text{OCH}_2\text{CH}_2)_3\text{OMe}$
	tetraglyme	tetraethyleneglycol dimethyl ether	$\text{Me}(\text{OCH}_2\text{CH}_2)_4\text{OMe}$
30	heptaglyme	heptaethyleneglycol dimethyl ether	$\text{Me}(\text{OCH}_2\text{CH}_2)_7\text{OMe}$
	tmeda	tetramethylethylenediamine	$\text{Me}_2\text{NCH}_2\text{CH}_2\text{NMe}_2$
35	pm deta	pentamethyldiethylenetriamine	$\text{Me}_2\text{NCH}_2\text{CH}_2\text{N}(\text{Me})\text{CH}_2\text{CH}_2\text{NMe}_2$
40	hmteta	hexamethyltriethylenetetramine	$\text{Me}_2\text{NCH}_2\text{CH}_2\{\text{N}(\text{Me})\text{CH}_2\text{CH}_2\}_2\text{NMe}_2$

- 18 -

In the accompanying drawings, Figures 1-7 are molecular structures determined by X-ray crystallography of selected compounds described in the Examples.

Figure 1 $[\text{La}(\text{thd})_3(\text{tetraglyme})]$ - example of type I
5 compound, see Example 10.

Figure 2 $[\text{Y}(\text{thd})_3]_2(\text{triglyme})$ - example of type II
compound, see Example 2.

Figure 3 $[\text{Y}(\text{thd})_3]_2(\text{hmteta})$ - example of type II
compound with polyamine adduct, see Example 5.

10 **Figure 4** $[\text{EuY}(\text{thd})_6(\text{triglyme})]$ - example of type II
compound with different metal atoms in a single structure,
see Example 7.

Figure 5 $[\text{Pr}(\text{thd})_3(\text{triglyme})][\text{Pr}(\text{thd})_3]_2(\text{triglyme})$ -
example of compound adopting type I and type II structure
15 simultaneously, see Example 17.

Figure 6 $[\text{Gd}(\text{thd})_3]_2(\text{heptaglyme})$ - example of type II
compound with added presence of two available glyme oxygen
atoms, see Example 34.

Figure 7 $[\{\text{Gd}(\text{thd})_3\}_2(\text{tetraglyme})]$ - example of a type
20 II compound, see Example 33.

Figure 8 $[\text{Ce}(\text{thd})_3(\text{dme})]$ - example of a type I
compound, see Example 14.

Figures 9-15 are thermogravimetric charts showing
properties such as melting and evaporation of examples of
25 compounds claimed.

- 19 -

Figure 9 [La(thd)₃(tetraglyme)] (a) heat flow (b) weight loss, product of Example 10.

Figure 10 [Eu(thd)₃]₂(triglyme) (a) heat flow (b) weight loss, product of Example 28.

5 **Figure 11** [Tb(thd)₃]₂(triglyme) (a) heat flow (b) weight loss, product of Example 38.

Figure 12 [EuY(thd)₆(triglyme)] (a) heat flow (b) weight loss, product of Example 7.

10 **Figure 13** [Pr(thd)₃(triglyme)][Pr(thd)₃]₂(triglyme) (a) heat flow (b) weight loss, product of Example 17.

Figure 14 [LaTm(thd)₆(triglyme)] (a) heat flow (b) weight loss, product of Example 13.

Figure 15 [Y(thd)₃]₂(hmteta) (a) heat flow (b) weight loss, product of Example 5.

The following Examples illustrate the invention. The x-ray crystal structures were generated with SHELX 91 using a local modification, DIFABS 2, operating on a PC. In the drawings (Figures 1-8), as is conventional, for clarity tert-
5 butyl groups are not shown. The differential scanning and thermogravimetric analyses (Figures 9-15) were determined on Polymer Laboratories PL 1500 simultaneous Thermal Analysis equipment.

- 20 -

EXAMPLES

1. YTTRIUM TRIS-THD DIGLYME $[Y(thd)_3(diglyme)]_2$ - an example of a type III compound.

Sodium hydroxide (12g, 300 mmole) is dissolved in 75 ml
5 methanol and stirred into a solution of thdH (55.2 g, 300 mmole) in 75 ml methanol. Then yttrium chloride hexahydrate (30.4 g, 100 mmole) is dissolved in 100 ml warm methanol and added portionwise with stirring to the thdNa solution. After completing the addition the solution is stirred for 10
10 minutes and then poured with vigorous stirring into 1 litre of water. The precipitated product is immediately filtered off, washed on the filter with water, turned into 100 ml hexane and warmed to dissolve. The organic solution is separated from residual water and insolubles, stripped until
15 solid begins to appear then set aside to crystallise. The product is filtered and vacuum dried as $[Y(thd)_3(H_2O)]_n$.

The $[Y(thd)_3(H_2O)]_n$ (57.5 g, 90 mmole) is dissolved with warming in 250 ml of hexane, diglyme (12 g, 90 mmole) is added and the solution stirred at room temperature for 1
20 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 61 g, 85% of colourless air stable crystals.

Melting point 86-89°C.

Microanalysis Found: C, 60.8; H, 9.2. Calcd. $YC_{39}H_{69}O_9$,
25 C, 61.1; H, 9.1 %.

- 21 -

^1H NMR in C_6D_6 at 270 MHz : δ 1.19 (s, CH_3), δ 3.22 (s, OCH_3), δ 3.41 (s, $\text{OCH}_2\text{-b}$), δ 3.57 (s, $\text{OCH}_2\text{-a}$), δ 5.82 (s, CH). Integral of thd:diglyme is 3:1.

Freezing point depression in benzene yields a molecular weight of 1490 ± 70 (calc. 1544).

2. YTTRIUM TRIS-THD TRIGLYME $[(\text{Y}(\text{thd})_3)_2(\text{triglyme})]$ - an example of a type II compound.

Yttrium isopropoxide (85g, 32 mmole) is dissolved in 250 ml of cyclohexane and then thdH (176g, 96 mmole) added and the solution refluxed for 2 hours. A short column is then fitted to the flask and the cyclo-hexane / isopropylalcohol azeotrope boiling at 68°C is removed. On cooling the product crystallises out and is then filtered and vacuum dried as $[\text{Y}(\text{thd})_3]_2$.

15 The $[\text{Y}(\text{thd})_3]_2$ (64.8 g, 100 mmole) is dissolved with warming in 200 ml of hexane, triglyme (8.6 g, 50 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

20 Yield is 65 g, 89% of colourless air stable crystals.

Melting point $77\text{--}81^\circ\text{C}$.

Microanalysis Found: C, 60.8; H, 9.2. Calcd. $\text{Y}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$, C, 61.1; H, 9.1 %.

- 22 -

Infrared spectrometry (Nujol ν cm^{-1}) : 1576(s), 1537(s), 1504 (s), 1490(s), 1422(s), 1302(m), 1250(m), 1223(s), 1180(s), 1137(s), 406(w).

^1H NMR in C_6D_6 at 270 MHz : δ 1.20 (s, CH_3), δ 3.26 (s, CH_3), δ 3.33 (s, $\text{OCH}_2\text{-c}$), δ 3.60 (s, $\text{OCH}_2\text{-b}$), δ 3.74 (s, $\text{OCH}_2\text{-a}$), δ 5.85 (s, CH). Integral of thd:triglyme is 6:1.

Freezing point depression in benzene yields a molecular weight of 1240 ± 75 (calc. 1276).

X-ray crystal structure - Figure 2.

10 3. YTTTRIUM TRIS-HFA TRIGLYME $[(\text{Y}(\text{hfa})_3)_2(\text{triglyme})]$ -
an example of a type II compound.

Yttrium hexamethyldisilazide (100g, 17.5 mmole) is dissolved in 400 ml of hexane and then hfaH (109g, 52.5 mmole) added and the solution refluxed for 2.5 hours. The
15 solvent and liberated hmdzH were removed under vacuum and the off-white solid recrystallised from chloroform-hexane. Yield of $[\text{Y}(\text{hfa})_3]_2$ is 102 g, 83%.

The $[\text{Y}(\text{hfa})_3]_2$ (50 g, 7.04 mmole) is dissolved with warming in 200 ml of hexane, triglyme (12.3 g, 7.04 mmole) is
20 added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 48 g, 77% of colourless air stable crystals.

Melting point $60\text{-}62^\circ\text{C}$.

- 23 -

Microanalysis Found: C, 27.5; H, 1.5. Calcd.

$Y_2C_{36}H_{20}F_{36}O_{15}$, C, 27.8; H, 1.3 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1572(s), 1533(m),
1500 (s), 1493(s), 1426(m), 1306(s), 1252(m), 1219(s),
5 1184(s), 1137(s), 404(w).

1H NMR in C_6D_6 at 270 MHz : δ 3.24 (s, OCH_3), δ 3.30 (s,
 OCH_2-c), δ 3.57 (s, OCH_2-b), δ 3.72 (s, OCH_2-a), δ 5.92 (s,
CH). Integral of hfa:triglyme is 6:1.

Freezing point depression in benzene yields a molecular
10 weight of 1530 ± 70 (calc. 1554).

4. YTTRIUM TRIS-TFA TETRAGLYME

$[(Y(tfa)_3)_2(tetraglyme)]$ - an example of a type II compound.

The Y_2O_3 as a finely ground powder (20 g, 88.5 mmole) is
suspended in 75 ml of toluene, containing tfaH (60 ml, 392
15 mmole) tetraglyme (39.2 ml, 177 mmole) is added and the
solution refluxed until > 90% of the metal oxide has
dissolved. It is then filtered and stripped to an oil and
set aside at 20°C to crystallise.

Yield is 41.5 g, 61% of colourless air stable crystals.
20 Melting point 74-76°C.

Microanalysis Found: C, 36.7; H, 3.8. Calcd.

$Y_2C_{40}H_{46}F_{18}O_{17}$, C, 36.4; H, 3.5 %.

1H NMR in C_6D_6 at 270 MHz : δ 1.26 (s, CH_3), δ 3.11 (s,
 OCH_3), δ 3.22 (s, OCH_2-d), δ 3.38 (s, OCH_2-c), δ 3.40 (s, OCH_2-

- 24 -

b), δ 3.44 (s, $\text{OCH}_2\text{-a}$), δ 5.91 (s, CH). Integral of tfa:tetraglyme is 6:1.

Freezing point depression in benzene yields a molecular weight of 1460 ± 80 (calc. 1498).

5 **5. YTTRIUM TRIS-THD HEXAMETHYLTRIETHYLENETETRAMINE**
[(Y(thd)₃),(HMTETA)] - an example of a type II compound.

The first part of the preparation employs a similar method to example 1, to yield $[\text{Y}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Y}(\text{thd})_3(\text{H}_2\text{O})]_n$ (0.72 g, 1.09 mmole) is dissolved
10 with warming in 10 ml of hexane, hmteta (0.29 ml, 1.09 mmole)
is added and the solution stirred at room temperature for 1
hour. It is then stripped to an oil and set aside at 20°C to
crystallise.

Yield is 0.76 g, 92% of colourless air stable crystals.

15 Melting point 109-112°C.

Microanalysis Found: C, 61.9; H, 9.5. Calcd.

$\text{Y}_2\text{C}_{78}\text{H}_{144}\text{O}_{12}\text{N}_4$, C, 62.2; H, 9.6 %.

¹H NMR in C_6D_6 at 270 MHz : δ 1.20 (s, CH_3), δ 2.21 (s, NMe), δ 2.34 (s, NMe_2), δ 2.59 (d, NCH_2), δ 5.86 (s, CH).

20 Integral of thd:hmteta is 6:1.

Sublimation : The complex sublimes intact in essentially quantitative yield in the range 90-110°C at 5×10^{-3} torr.

Freezing point depression in benzene yields a molecular weight of 1475 ± 50 (calc. 1506).

25 X-ray crystal structure - Figure 3.

- 25 -

6. YTTTRIUM TRIS-Ph₂ACAC TETRAMETHYLETHYLENEDIAMINE
[Y(Ph₂acac)₃(TMEDA)] - an example of a type I compound.

The first part of the preparation employs a similar method to example 3, to yield [Y(Ph₂acac)₃]_n.

5 The [Y(Ph₂acac)₃]_n (4.0 g, 5.28 mmole) is suspended in 50 ml of chloroform, tmeda (0.62 ml, 5.28 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 4.25 g, 92% of colourless air stable crystals.

10 Melting point 160-163°C.

Microanalysis Found: C, 70.2; H, 5.9. Calcd. YC₅₁H₄₉O₆N₂, C, 70.0; H, 5.6 %.

¹H NMR in CDCl₃ at 270 MHz : δ 2.08 (s, NMe), δ 2.27 (s, NMe₂), δ 5.86 (s, CH), δ 7.06 (m, Ph), δ 7.18 (m, Ph), δ 7.34
15 (m, Ph). Integral of Ph₂acac:tmeda is 3:1.

Mass Spectrometry (EI⁺): 874 [Y(Ph₂acac)₃(tmeda)]⁺ (7%),
754 [Y((Ph₂acac)₃)]⁺ (34%) and lower mass species.

7. YTTTRIUM-EUROPIUM TRIS-THD TRIGLYME
[YEu(thd)₃(triglyme)] -an example of a type II compound with
20 two different metals.

The first part of the preparation employs a similar method to example 1, the quantities being sodium hydroxide (12g, 300 mmole), thdH (55.2 g, 300 mmole), europium chloride hexahydrate (23.7g, 50 mmole) and yttrium chloride

- 26 -

hexahydrate (15.2 g, 50 mmole) to yield $[Y(thd)_3(H_2O)]_6$ and $[Eu(thd)_3(H_2O)]_6$.

The $[Y(thd)_3(H_2O)]_6$ (28.8 g, 45 mmole) and $[Eu(thd)_3(H_2O)]_6$ (31.5 g, 45 mmole) are dissolved on with
5 warming in 250 ml of hexane, triglyme (8 g, 45 mmole) is added and the solution stirred at room temperature for 1 hour. It is then set stripped to an oil and set aside at 20°C to crystallise.

Yield is 62 g, 87% of colourless air stable crystals.

10 Melting point 95-97°C.

Microanalysis Found: C, 56.4; H, 8.2. Calcd. $YEuC_{74}H_{132}O_{16}$, C, 56.1; H, 8.1 %.

1H NMR in C_6D_6 at 270 MHz : δ -0.52 (s, CH_3), δ 0.4 (s, br, OCH_3), δ 1.26 (s, CH_3), δ 8.0 (s, $OCH_2-c + b$), δ 9.47 (s,
15 OCH_2-a), δ 5.99 (s, CH). Integral of thd:triglyme is 6:1.

Freezing point depression in benzene yields a molecular weight of 1470 ± 75 (calc. 1519).

Differential scanning analysis and thermogravimetric analysis see Figures 12a and 12b.

20 X-ray crystal structure - Figure 4.

8. YTTRIUM-TERBIUM TRIS-THD TRIGLYME

$[YTb(thd)_6(triglyme)]$ -an example of a type II compound with two different metals.

The first part of the preparation employs a similar
25 method to example 1, the quantities being sodium hydroxide

- 27 -

(12g, 300 mmole), thdH (55.2 g, 300 mmole), terbium chloride hexahydrate (24.0g, 50 mmole) and yttrium chloride hexahydrate (15.2 g, 50 mmole) to yield $[Y(thd)_3(H_2O)]_n$ and $[Tb(thd)_3(H_2O)]_n$.

5 The $[Y(thd)_3(H_2O)]_n$ (28.8 g, 45 mmole) and $[Tb(thd)_3(H_2O)]_n$ (32.6 g, 45 mmole) are dissolved with warming in 200 ml of hexane, triglyme (8 g, 45 mmole) is added and the solution stirred at room temperature for 1 hour. It is then set stripped to an oil and set aside at 20°C to crystallise.

10 Yield is 51 g, 82% of colourless air stable crystals. Melting point 88-90°C.

Microanalysis Found: C, 58.6; H, 8.9. Calcd. $YTbC_{74}H_{132}O_{16}$, C, 58.3; H, 8.7 %.

1H NMR in C_6D_6 at 270 MHz : δ -0.84 (s, CH_3), δ 0.1 (s, br, OCH_3), δ 1.19 (s, CH_3), δ 7.3 (s, $OCH_2-c + b$), δ 9.12 (s, OCH_2-a), δ 5.44 (s, CH). Integral of thd:triglyme is 6:1.

15

Freezing point depression in benzene yields a molecular weight of 1440 ± 60 (calc. 1526).

9. LANTHANUM TRIS-THD TRIGLYME $[La(thd)_3(triglyme)]$ -
20 an example of a type I compound.

The first part of the preparation employs a similar method to example 1, to yield $[La(thd)_3(H_2O)]_n$.

The $[La(thd)_3(H_2O)]_n$ (20 g, 28 mmole) is dissolved with warming in 200 ml of hexane, triglyme (5.0 g, 28 mmole) is
25 added and the solution stirred at room temperature for 1

- 28 -

hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 20.5 g, 82% of pale-yellow air stable crystals.

Melting point 80-83°C.

5 Microanalysis Found: C, 57.0; H, 8.9. Calcd. $\text{LaC}_{41}\text{H}_{75}\text{O}_{10}$,
C, 56.8; H, 8.7 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1608(s), 1586(s),
1575(s), 1536(s), 1504 (s), 1451(s), 1417(s), 1388(m),
1358(s), 1137(s), 403(w).

10 ^1H NMR in C_6D_6 at 270 MHz : δ 1.19 (s, CH_3), δ 3.22 (s,
 OCH_3), δ 3.31 (s, $\text{OCH}_2\text{-c}$), δ 3.57 (s, $\text{OCH}_2\text{-b}$), δ 3.69 (s, $\text{OCH}_2\text{-}$
a), δ 5.82 (s, CH). Integral of thd:triglyme is 3:1.

Freezing point depression in benzene yields a molecular
weight of 880 ± 40 (calc. 866).

15 10. LANTHANUM TRIS-THD TETRAGLYME

[$\text{La}(\text{thd})_3(\text{tetraglyme})$] - an example of a type I compound.

Sodium hydroxide (11g, 275 mmole) is dissolved in 75 ml
methanol and stirred into a solution of thdH (50.6 g, 275
mmole) in 75 ml methanol. Then lanthanum chloride

20 heptahydrate (34 g, 91 mmole) is dissolved in 100 ml warm
methanol and added portionwise with stirring to the thdNa
solution. After completing the addition the solution is
stirred for 10 minutes and then poured with vigorous stirring
into 1 litre of water. The precipitated product is

25 immediately filtered off, washed on the filter with water,

- 29 -

turned into 100 ml hexane and warmed to dissolve. The organic solution is separated from residual water and insolubles, stripped until solid begins to appear then set aside to crystallise. The product is filtered and vacuum
5 dried as $[\text{La}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{La}(\text{thd})_3(\text{H}_2\text{O})]_n$ (57 g, 82 mmole) is dissolved with warming in 250 ml of hexane, tetraglyme (18.2 g, 82 mmole) is added and the solution stirred at room temperature for 1 hour. It is then set stripped to an oil and set aside at
10 20°C to crystallise.

Yield is 75 g, 90% of pale yellow air stable crystals.

Melting point 41-44°C.

Microanalysis Found: C, 57.0; H, 8.5. Calculated, C, 56.7; H, 8.7 %.

15 ^1H NMR in C_6D_6 at 270 MHz : δ 1.18 (s, CH_3), δ 3.09 (s, CH_3), δ 3.26 (s, $\text{OCH}_2\text{-d}$), δ 3.41 (s, $\text{OCH}_2\text{-c}$), δ 3.43 (s, $\text{OCH}_2\text{-b}$), δ .46 (s, $\text{OCH}_2\text{-a}$), δ 5.74 (s, CH). Integral of thd:tetraglyme is 3:1.

Freezing point depression in benzene yields a molecular
20 weight of 865 ± 60 (calc. 911).

Differential scanning analysis and thermogravimetric analysis see figures 9a and 9b.

X-ray crystal structure - Figure 1.

- 30 -

11. LANTHANUM TRIS-HFA HEPTAGLYME

$[(\text{La}(\text{hfa})_3)_2(\text{heptaglyme})]$ - an example of a type II compound.

The $[\text{La}(\text{hfa})_3]_2$ was prepared by a similar method to that described in example 2. The $[\text{La}(\text{hfa})_3]_2$ (10 g, 14.1 mmole) is dissolved with warming in 200 ml of hexane, heptaglyme (5.0 g, 14.1 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 9.2 g, 61% of colourless air stable crystals.

Melting point 57-60°C.

Microanalysis Found: C, 26.7; H, 2.3. Calcd.

$\text{La}_2\text{C}_{46}\text{H}_{40}\text{O}_{20}\text{F}_{36}$, C, 29.5; H, 2.1 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1590(m), 1574(s), 1530(s), 1502 (s), 1486(s), 1420(s), 1343(m), 1230(m), 1221(s), 1178(s), 1134(s), 405(w).

^1H NMR in C_6D_6 at 270 MHz : δ 3.04 (s, OCH_3), δ 3.17 (m, $\text{OCH}_2\text{-e+f}$), δ 3.29 (m, $\text{OCH}_2\text{-c+d}$), δ 3.41 (s, $\text{OCH}_2\text{-b}$), δ 3.44 (s, $\text{OCH}_2\text{-a}$), δ 5.90 (s, CH). Integral of hfa:heptaglyme is 6:1.

Freezing point depression in benzene yields a molecular weight of 1830 ± 90 (calc. 1874).

12. LANTHANUM TRIS-ACAC TETRAGLYME

$[\text{La}(\text{acac})_3(\text{tetraglyme})]$ - an example of a type I compound.

The $[\text{La}(\text{acac})_3]_2$ was prepared by a similar method to that described in example 3. The $[\text{La}(\text{acac})_3]_2$ (3 g, 6.6 mmole) is

- 31 -

dissolved with warming in 50 ml of hexane, tetraglyme (1.5 g, 6.6 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

5 Yield is 2.55 g, 56 % of colourless air stable crystals.

Melting point decomp > 250°C.

Microanalysis Found: C, 45.8; H, 6.7. Calcd. $\text{LaC}_{25}\text{H}_{43}\text{O}_{11}$, C, 45.6; H, 6.5 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1591(m), 1572(s),
 10 1532(s), 1504 (s), 1488(s), 1422(s), 1344(m), 1232(m),
 1220(s), 1176(s), 1135(s), 404(w).

^1H NMR in CDCl_3 at 270 MHz : δ 0.98 (s, CH_3), δ 3.06 (s, OCH_3), δ 3.20 (s, $\text{OCH}_2\text{-d}$), δ 3.42 (m, $\text{OCH}_2\text{-c}$), δ 3.47 (s, $\text{OCH}_2\text{-b}$), δ 3.62 (s, $\text{OCH}_2\text{-a}$), δ 5.83 (s, CH). Integral of
 15 acac:tetraglyme is 3:1.

13. LANTHANUM-THULIUM TRIS-THD TRIGLYME

$[\text{LaTm}(\text{thd})_3(\text{triglyme})]$ - an example of a $\text{t@DEdDGDIDK}^{\wedge}\text{F}$ δ 1.22 (s, CH_3), δ 5.81 (s, CH_{La}), δ 6.35 (s, CH_{Tm}), δ 7.84 (s, $\text{OCH}_2\text{-c} + \text{b}$), δ 14.02 (s, $\text{OCH}_2\text{-a}$). Integral of thd:triglyme is 6:1.

20 Sublimation behaviour : This complex remains intact on high vacuum sublimation and sublimes in near quantitative yield in the range 110-135°C.

Freezing point depression in benzene yields a molecular weight of 1520 ± 85 (calc. 1584).

- 32 -

14. CERIUM TRIS-THD DIMETHOXYETHANE $[\text{Ce}(\text{thd})_3(\text{dme})]$ -
an example of a type I compound.

Sodium hydroxide (11g, 275 mmole) is dissolved in 50 ml of 95% ethanol and stirred into a solution of thdH (50.6 g, 275 mmole) in 75 ml methanol. Then cerium chloride heptahydrate (34.3 g, 91 mmole) and 1.2 equivalents of dimethoxyethane (dme) was dissolved in 50 ml of 50% ethanol and added portionwise with stirring to the thdNa solution. After completing the addition the solution is stirred for 10 minutes and the crude product precipitates out as a pale-brown solid. This was recrystallised from hot chloroform to produce a pale-brown crystalline solid.

Yield is 24 g, 75% of pale-brown air stable crystals.

Melting point : Does not melt below 250°C.

15 Microanalysis Found: C, 57.0; H, 9.1. Calcd. $\text{CeC}_{37}\text{H}_{69}\text{O}_8$, C, 56.9; H, 8.8 %.

^1H NMR in CDCl_3 at 270 MHz : δ 1.17 (s, CH_3), δ 3.06 (s, OCH_3), δ 3.22 (s, OCH_2), δ 5.83 (s, CH). Integral of thd:dme is 3:1

20 Freezing point depression in benzene yields a molecular weight of 760 ± 35 (calc. 781).

X-ray crystal structure - Figure 8.

15. CERIUM TRIS-THD TETRAMETHYLETHYLENEDIAMINE $[\text{Ce}(\text{thd})_3(\text{TMEDA})]$ - an example of a type I compound.

- 33 -

The preparation is identical to that used in example 14, except for the addition of 1.2 equivalents of tetramethylethylenediamine (tmeda) to the ethanolic cerium chloride solution to yield a pale-brown solid. This was
5 recrystallised from hot chloroform to produce a pale-brown crystalline solid.

Yield is 33 g, 79 % of pale-brown air stable crystals.

Melting point : 190-193°C.

Microanalysis Found: C, 58.1; H, 9.4. Calcd. $\text{CeC}_{39}\text{H}_{75}\text{O}_6\text{N}_2$,
10 C, 58.0; H, 9.3 %.

^1H NMR in CDCl_3 at 270 MHz : δ 1.18 (s, CH_3), δ 2.07 (s, NMe_2), δ 3.14 (s, NCH_2), δ 5.82 (s, CH). Integral of thd:tmeda is 3:1.

Freezing point depression in benzene yields a molecular
15 weight of 780 ± 40 (calc. 807).

16. CERIUM TRIS-THD TRIGLYME $[\text{Ce}(\text{thd})_3(\text{triglyme})]$ - an example of a type I compound.

The preparation is identical to that used in example 14, except for the addition of 1.2 equivalents of triglyme to the
20 ethanolic cerium chloride solution to yield a pale-brown solid. This was recrystallised from hot chloroform to produce a brown crystalline solid.

Yield is 33 g, 79 % of brown air stable crystals.

Melting point : 90-96°C but possibly dissolving in
25 liberated glyme.

- 34 -

Microanalysis Found: C, 57.0; H, 9.2. Calcd. $\text{CeC}_{41}\text{H}_{77}\text{O}_{10}$,
C, 56.6; H, 8.9 %.

^1H NMR in CDCl_3 at 270 MHz : δ 1.22 (s, CH_3), δ 3.22 (s,
 OCH_3), δ 3.30 (s, $\text{OCH}_2\text{-c}$), δ 3.56 (s, $\text{OCH}_2\text{-b}$), δ 3.68 (s,
5 $\text{OCH}_2\text{-a}$), δ 5.8s (s, CH). Integral of thd:triglyme is 3:1

Freezing point depression in benzene yields a molecular
weight of 845 ± 50 (calc. 869).

17. PRASEODYMIUM TRIS-THD TRIGLYME

$[\text{Pr}(\text{thd})_3(\text{triglyme})][(\text{Pr}(\text{thd})_3)_2(\text{triglyme})]$ - an example of a
10 mixed type I / II compound.

The first part of the preparation employs a similar
method to example 1, the quantities being sodium hydroxide
(12g, 300 mmole), thdH (55.2 g, 300 mmole) and praseodymium
chloride hexahydrate (29.5 g, 100 mmole) to yield
15 $[\text{Pr}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Pr}(\text{thd})_3(\text{H}_2\text{O})]_n$ (55.6 g, 90 mmole) was dissolved
with warming in 250 ml of hexane, triglyme (8 g, 45 mmole) is
added and the solution stirred at room temperature for 1
hour. It is then stripped to an oil and set aside at 20°C to
20 crystallise.

Yield is 61 g, 82 % of pale green air stable crystals.

Melting point $74\text{-}77^\circ\text{C}$.

Microanalysis Found: C, 56.8; H, 8.6. Calcd. , C, 56.7;
H, 8.6 %.

- 35 -

Freezing point depression in benzene yields a molecular weight of 1470 ± 75 (calc. 1519).

Differential scanning analysis and thermogravimetric analysis see Figures 13a and 13b.

5 X-ray crystal structure - Figure 5.

18. PRASEODYMIUM TRIS-THD TETRAGLYME

$[\text{Pr}(\text{thd})_3(\text{tetraglyme})]$ - an example of a type I compound.

The preparation of $[\text{Pr}(\text{thd})_3(\text{H}_2\text{O})]_n$ is similar to the method used for example 1. The $[\text{Pr}(\text{thd})_3(\text{H}_2\text{O})]_n$ (60 g, 85
10 mmole) was dissolved with warming in 200 ml of hexane, tetraglyme (9.3 g, 42 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 63 g, 91 % of pale green air stable crystals.

15 Melting point 83-86°C.

Microanalysis Found: C, 56.7; H, 8.9. Calcd. $\text{PrC}_{43}\text{H}_{79}\text{O}_{11}$, C, 56.6; H, 8.7 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1607(m), 1587(s),
1573(m), 1538(s), 1502 (m), 1450(s), 1423(m), 1383(s),
20 1354(m), 1140(s), 402(w).

Freezing point depression in benzene yields a molecular weight of 875 ± 44 (calc. 912).

19. PRASEODYMIUM TRIS-THD HMTETA

$[\text{Pr}(\text{thd})_3(\text{HMTETA})][(\text{Pr}(\text{thd})_3)_2(\text{HMTETA})]$ - an example of a
25 mixed type I / II compound.

- 36 -

The preparation of $[\text{Pr}(\text{thd})_3(\text{H}_2\text{O})]_n$ is similar to the method used for example 1. The $[\text{Pr}(\text{thd})_3(\text{H}_2\text{O})]_n$ (90 g, 127.5 mmole) was dissolved with warming in 300 ml of hexane, hmteta (29.25 g, 127.5 mmole) is added and the solution stirred at
5 room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 160.5 g, 76 % of pale green air stable crystals.

Melting point: 150-152°C.

10 Microanalysis Found: C, 61.4; H, 9.7. Calcd.

$\text{Pr}_3\text{C}_{123}\text{H}_{231}\text{O}_{18}\text{N}_8$, C, 61.8; H, 9.7 %.

Freezing point depression in benzene yields a molecular weight of 875±44 (calc. 912).

Mass Spectrometry (EI^+) : 1469 $[\text{Pr}_2(\text{thd})_6(\text{hmteta})]^+$ (3%),
15 1286 $[\text{Pr}_2(\text{thd})_5(\text{hmteta})]^+$ (2%), 920 $[\text{Pr}(\text{thd})_3(\text{hmteta})]^+$ (8%),
690 $[\text{Pr}(\text{thd})_3]^+$ (70%).

20. PRASEODYMIUM TRIS-HFA DIGLYME $[\text{Pr}(\text{hfa})_3(\text{diglyme})]_2$ -
an example of a type III compound.

The preparation of $[\text{Pr}(\text{hfa})_3(\text{H}_2\text{O})]_n$ is similar to the
20 method used for example 1. The $[\text{Pr}(\text{hfa})_3(\text{H}_2\text{O})]_n$ (100 g, 128 mmole) was dissolved with warming in 500 ml of hexane, diglyme (17.1 g, 128 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

25 Yield is 103 g, 87 % of green air stable crystals.

- 37 -

Melting point 85-88°C.

Microanalysis Found: C, 28.3; H, 1.8. Calcd.

$\text{PrC}_{21}\text{H}_{17}\text{O}_9\text{F}_{18}$, C, 28.1; H, 1.7 %.

Freezing point depression in benzene yields a molecular weight of 875 ± 44 (calc. 912).

Mass Spectrometry (EI^+) : 896 $[\text{Pr}(\text{hfa})_3(\text{diglyme})]^+$ (14%), 762 $[\text{Pr}(\text{hfa})_3]^+$ (71%) and lower mass ions containing hfa fragments.

21. PRASEODYMIUM TRIS-HFA PMDETA $[\text{Pr}(\text{hfa})_3(\text{pmdeta})]$ -
10 an example of a type I compound.

The preparation of $[\text{Pr}(\text{hfa})_3(\text{H}_2\text{O})]_n$ is similar to the method used for example 1. The $[\text{Pr}(\text{hfa})_3(\text{H}_2\text{O})]_n$ (75 g, 96 mmole) was dissolved with warming in 250 ml of hexane, pmdeta (16.5 g, 96 mmole) is added and the solution stirred at room
15 temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 62 g, 68 % of light green air stable crystals.

Melting point > 250°C.

Microanalysis Found: C, 31.0; H, 2.9. Calcd.

20 $\text{PrC}_{24}\text{H}_{26}\text{O}_6\text{F}_{18}\text{N}_3$, C, 30.8; H, 2.8 %.

Mass Spectrometry (EI^+) : 935 $[\text{Pr}(\text{hfa})_3(\text{pmdeta})]^+$ (18%), 762 $[\text{Pr}(\text{hfa})_3]^+$ (64%) and lower mass ions containing hfa fragments.

22. NEODYMIUM TRIS-THD DIGLYME $[\text{Nd}(\text{thd})_3(\text{diglyme})]_2$ -
25 an example of a type III compound.

- 38 -

The preparation of $[\text{Nd}(\text{thd})_3(\text{H}_2\text{O})]_n$ is similar to the method used for example 1. The $[\text{Nd}(\text{thd})_3(\text{H}_2\text{O})]_n$ (12.5 g, 17.6 mmole) is dissolved with warming in 250 ml of hexane, diglyme (2.35 g, 17.6 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 10.8 g, 73% of pink air stable crystals.

Melting point 111-113°C.

Microanalysis Found: C, 56.8; H, 8.4. Calcd. $\text{NdC}_{39}\text{H}_{39}\text{O}_6$,
10 C, 56.6; H, 8.3 %.

^1H NMR in C_6D_6 at 270 MHz : δ -1.22 (s, br, CH_3), δ 0.13 (s, br, OCH_3), δ 1.32 (s, CH), δ 7.14 (s, br, $\text{OCH}_2\text{-b}$), δ 9.36 (s, br, $\text{OCH}_2\text{-a}$). Integral of thd:diglyme is 3:1.

Freezing point depression in benzene yields a molecular
15 weight of 790 ± 40 (calc. 827).

23. NEODYMIUM TRIS-THD TRIGLYME $[\{\text{Nd}(\text{thd})_3\}_2(\text{triglyme})]$

- an example of a type II compound.

The preparation of $[\text{Nd}(\text{thd})_3(\text{H}_2\text{O})]_n$ is similar to the method used for example 1. The $[\text{Nd}(\text{thd})_3(\text{H}_2\text{O})]_n$ (25 g, 35.2 mmole) is dissolved with warming in 250 ml of hexane, triglyme (6.3 g, 35.2 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 19.3 g, 62% of pink air stable crystals.

25 Melting point 74-77°C.

- 39 -

Microanalysis Found: C, 57.2; H, 8.6. Calcd. $\text{Nd}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$,
C, 56.8; H, 8.4 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1604(s), 1583(m),
1572(s), 1534(s), 1503 (m), 1447(m), 1418(s), 1393(m),
5 1356(s), 1135(s), 407(w).

^1H NMR in C_6D_6 at 270 MHz : δ -1.74 (s, br, CH_3), δ -0.87
(s, OCH_3), δ 8.22 (s, $\text{OCH}_2\text{-c}$), δ 9.04 (s, $\text{OCH}_2\text{-b}$), δ 11.78
(s, $\text{OCH}_2\text{-a}$). Integral of thd:triglyme is 6:1. Note the CH
signal is not observed.

10 Freezing point depression in benzene yields a molecular
weight of 1525 ± 73 (calc. 1564).

24. NEODYMIUM TRIS- Ph_2acac TETRAGLYME

$[\text{Nd}(\text{Ph}_2\text{acac})_3(\text{tetraglyme})]$ - an example of a type I compound.

The preparation of $[\text{Nd}(\text{Ph}_2\text{acac})_3]_n$ is similar to the
15 method used for example 3. The quantities used are
 $[\text{Nd}(\text{hmdz})_3]_n$ (15 g, 24.0 mmole), Ph_2acacH (16.1 g, 72 mmole)
and tetraglyme (5.3 g, 24 mmole).

Yield is 22.8 g, 91% of pink air stable crystals.

Melting point $> 250^\circ\text{C}$.

20 Microanalysis Found: C, 64.2; H, 5.5. Calcd. $\text{NdC}_{55}\text{H}_{55}\text{O}_{11}$,
C, 63.8; H, 5.3 %.

^1H NMR in CDCl_3 at 270 MHz : δ 0.12 (s, br, OCH_3), δ 2.14
(s, br, Ph), δ 2.66 (s, br, Ph), δ 3.44 (s, br, Ph) δ 7.60 (s,
br, $\text{OCH}_2\text{-c}$), δ 8.83 (s, br, $\text{OCH}_2\text{-b}$), δ 10.45 (s, br, $\text{OCH}_2\text{-a}$).

- 40 -

Integral of Ph₂acac:tetraglyme is 6:1. Note the CH signal is not observed.

25. SAMARIUM TRIS-THD DIMETHOXYETHANE [Sm(thd)₃(DME)] - an example of a type I compound.

5 The preparation is similar to that used in example 14, except for the addition of 1.1 equivalents of dimethoxyethane (dme) (1.92 g 21.1 mmole) to the ethanolic samrium chloride solution (7.0 g 19.2 mmole), which is subsequently added to the thdNa solution (11.9 ml 57.6mmole) to yield a pale-yellow solution. This was then stripped to an oil and set aside at 20°C to crystallise.

Yield is 10.7 g, 71% of pale-yellow air stable crystals.

Melting point : 96-98°C.

Microanalysis Found: C, 56.6; H, 8.9. Calcd. SmC₃₇H₄₉O₈,
15 C, 56.2; H, 8.7 %.

Mass Spectrometry (EI⁺) : 790 [Sm(thd)₃(dme)]⁺ (3%), 700 [Sm(thd)₃]⁺ (53%).

26. SAMARIUM TRIS-HFA TETRAGLYME

[{Sm(hfa)₃}₂(tetraglyme)] - an example of a type II compound.

20 The preparation of [Sm(hfa)₃(H₂O)]₂ is similar to the method used for example 1. The [Sm(hfa)₃(H₂O)]₂ (3.0 g, 3.8 mmole) is dissolved with warming in 40 ml of hexane, tetraglyme (0.49 g, 3.8 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

- 41 -

Yield is 2.6 g, 74 % of light-yellow air stable crystals.

Melting point : 90-92°C.

Microanalysis Found: C, 27.7; H, 1.8. Calcd.

5 $\text{Sm}_2\text{C}_{40}\text{H}_{28}\text{O}_{17}\text{F}_{36}$, C, 27.2; H, 1.6 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1611(s), 1590(m), 1575(s), 1531s), 1502(s), 1441(m), 1419(s), 1379(m), 1349(s), 1130(s), 409(w).

Freezing point depression in benzene yields a molecular
10 weight of 1710 ± 90 (calc. 1765).

27. SAMARIUM TRIS-ACAC HEPTAGLYME

$[\{\text{Sm}(\text{thd})_3\}_2(\text{heptaglyme})]$ - an example of a type II compound.

The preparation of $[\text{Sm}(\text{acac})_3]_6$ is similar to the method used for example 3. The quantities used are $[\text{Sm}(\text{hmdz})_3]_6$ (4
15 g, 6.03 mmole), acacH (1.8 g, 18.1 mmole) and heptaglyme (2.2 g, 6.03 mmole). The solution is stirred at room temperature for 1 hour and then stripped to an oil and set aside at 20°C to crystallise.

Yield is 5.4 g, 71.1% of yellow air stable crystals.

20 Melting point : decomp $>250^\circ\text{C}$.

Microanalysis Found: C, 44.5; H, 5.9. Calcd. $\text{Sm}_2\text{C}_{46}\text{H}_{76}\text{O}_{20}$, C, 44.2; H, 6.1 %.

Mass Spectrometry (EI^+) : 1249 $[\text{Sm}_2(\text{acac})_6(\text{heptaglyme})]^+$ (1%), 796 $[\text{Sm}_2(\text{acac})_3]^+$ (61%), 700 $[\text{Sm}(\text{thd})_3]^+$ (16%) and lower
25 mass ions.

- 42 -

28. EUROPIUM TRIS-THD TRIGLYME [(Eu(thd)₃)₂(triglyme)]

- an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield [Eu(thd)₃(H₂O)]_n.

5 The [Eu(thd)₃(H₂O)]_n (57.5 g, 90 mmole) is dissolved with warming in 250 ml of hexane, triglyme (8 g, 45 mmole) is added and the solution stirred at room temperature for 1 hour. It is then set stripped to an oil and set aside at 20°C to crystallise.

10 Yield is 63.4 g, 97% of pale-yellow air stable crystals. Melting point 111-114°C.

Microanalysis Found: C, 55.8; H, 8.2. Calcd. Eu₂C₇₄H₁₃₂O₁₆, C, 55.7; H, 8.3 %.

¹H NMR in C₆D₆ at 270 MHz : δ -0.55 (s, br, CH₃), δ -0.35
15 (s, OCH₃), δ 8.99 (s, OCH₂-a), δ 10.26 (s, OCH₂-b), δ 11.05 (s, OCH₂-c+d). Integral of thd:triglyme is 6:1.

Freezing point depression in benzene yields a molecular weight of 1529±75 (calc. 1580).

Differential scanning analysis and thermogravimetric
20 analysis see Figures 10a and 10b.

29. EUROPIUM TRIS-THD TETRAGLYME

[(Eu(thd)₃)₂(tetraglyme)] - an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield [Eu(thd)₃(H₂O)]_n.

- 43 -

The $[\text{Eu}(\text{thd})_3(\text{H}_2\text{O})]_n$ (80.0 g, 111 mmole) is dissolved with warming in 400 ml of hexane, tetraglyme (12.2 g, 55 mmole) is added and the solution stirred at room temperature for 1 hour. It is then set stripped to an oil and set aside at 5 20°C to crystallise.

Yield is 79.1 g, 86% of pale-yellow air stable crystals.

Melting point 98-100°C.

Microanalysis Found: C, 56.1; H, 8.6. Calcd. $\text{Eu}_2\text{C}_{82}\text{H}_{78}\text{O}_{20}$, C, 55.7; H, 8.3 %.

10 ^1H NMR in C_6D_6 at 270 MHz : δ -1.04 (s, br, CH_3), δ 0.12 (s, OCH_3), δ 8.36 (s, $\text{OCH}_2\text{-a}$), δ 9.61 (s, $\text{OCH}_2\text{-b}$), δ 12.13 (s, $\text{OCH}_2\text{-c+d}$). Integral of thd:tetraglyme is 6:1.

Freezing point depression in benzene yields a molecular weight of 1570 ± 78 (calc. 1624).

15 30. GADOLINIUM TRIS-THD DIMETHOXYETHANE

$[\text{Gd}(\text{thd})_3(\text{dme})]$ - an example of a type I compound.

The first part of the preparation employs a similar method to example 1 to yield $[\text{Gd}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Gd}(\text{thd})_3(\text{H}_2\text{O})]_n$ (40.0 g, 55.23 mmole) is dissolved 20 with warming in 400 ml of hexane, and the solution stirred at for 15 min. The solvent is then removed under vacuum to yield an off-white solid, which is redissolved in 50ml of hot hexane to give the $[\text{Gd}_2(\text{thd})_6]$ as white needles.

Yield is 37.2 g, 96% of colourless air stable crystals.

25 Melting point 176-178°C.

- 44 -

Microanalysis Found: C, 56.9; H, 8.3. Calcd. $\text{GdC}_{33}\text{H}_{57}\text{O}_6$,
C, 56.1; H, 8.2 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1580(m), 1571(m),
1538(m), 1501 (m), 1403(s), 1355(vs), 1180(m), 1132(w),
5 475(w), 405(w).

Freezing point depression in benzene yields a molecular
weight of 1380 ± 45 (calc. 1414).

Mass Spectrometry (EI^+) : 707 $[\text{Gd}(\text{thd})_3]^+$ (1%), 651
 $[\text{Gd}(\text{thd})_2(\text{Bu}'\text{COCHCO})]^+$ (26%), 524 $[\text{Gd}(\text{thd})_2]^+$ (100%) and lower
10 mass ions.

X-ray analysis has confirmed that the molecule is a
dimer.

The $[\text{Gd}_2(\text{thd})_6]$ (10.0 g, 7.0 mmole) is dissolved with
warming in 80 ml of hexane, dme (0.25 ml, 7.0 mmole) is added
15 and the solution stirred at room temperature for 1 hour. The
solution was then left for 24 hs. at -20°C to crystallise.

Yield is 9.7 g, 95 % of colourless air stable crystals.

Melting point shows evidence of dissolution in the dme
ligand $117-130^\circ\text{C}$.

20 Microanalysis Found: C, 55.9; H, 8.6. Calcd. $\text{GdC}_{37}\text{H}_{67}\text{O}_8$,
C, 55.7; H, 8.5 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1588(s), 1575(s),
1538(s), 1505 (s), 1418(s), 1357(s), 1197(m), 1139(w),
475(w), 407(w).

- 45 -

Mass Spectrometry (EI^+) : 797 $[\text{Gd}(\text{thd})_3(\text{dme})]$ (1%),
707 $[\text{Gd}(\text{thd})_3]^+$ (37%), 651 $[\text{Gd}(\text{thd})_2(\text{Bu}^t\text{COCHCO})]^+$ (26%), 524
 $[\text{Gd}(\text{thd})_2]^+$ (100%) and lower mass ions.

X-ray analysis has confirmed that the molecule is an
5 eight coordinate monomer, $[\text{Gd}(\text{thd})_3(\text{dme})]$.

31. GADOLINIUM TRIS-THD DIGLYME $[\text{Gd}(\text{thd})_3(\text{diglyme})]_2$ -
an example of a type III compound.

The $[\text{Gd}(\text{thd})_3]_2$ {prepared via examples 1 and 30} (10.0 g,
7.0 mmole) is dissolved with warming in 80 ml of hexane,
10 diglyme (1.75 ml, 14.0 mmole) is added and the solution
stirred at room temperature for 1 hour. The solution was
then left for 24 hs. at -20°C to crystallise.

Yield is 9.3 g, 86 % of colourless air stable crystals.

Melting point $77-79^\circ\text{C}$.

15 Microanalysis Found: C, 56.0; H, 8.6. Calcd. $\text{GdC}_{39}\text{H}_{71}\text{O}_9$,
C, 55.7; H, 8.5 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1577(vs),
1536(s), 1505 (vs), 1456(vs), 1376(s), 1180(m), 1139(s),
476(m), 398(w).

20 Mass Spectrometry (EI^+) : 797 $[\text{Gd}(\text{thd})_3(\text{dme})]$ (1%),
707 $[\text{Gd}(\text{thd})_3]^+$ (37%), 651 $[\text{Gd}(\text{thd})_2(\text{Bu}^t\text{COCHCO})]^+$ (26%), 524
 $[\text{Gd}(\text{thd})_2]^+$ (100%) and lower mass ions.

32. GADOLINIUM TRIS-THD TRIGLYME
 $[\{\text{Gd}(\text{thd})_3\}_2(\text{triglyme})]$ - an example of a type II compound.

- 46 -

The $[\text{Gd}(\text{thd})_3]_2$ {prepared via examples 1 and 30} (10.0 g, 7.0 mmole) is dissolved with warming in 80 ml of hexane, triglyme (2.60 ml, 14.0 mmole) is added and the solution stirred at room temperature for 1 hour. The solvent was then removed yielding an oil, from which over a period of 24 hrs. at -20°C colourless crystals formed.

Yield is quantitative of colourless air stable crystals. Melting point $87-89^\circ\text{C}$.

Microanalysis Found: C, 55.7; H, 8.2. Calcd. $\text{Gd}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$,
10 C, 55.8; H, 8.3 %.

Infrared spectrometry ($\text{Nujol } \nu \text{ cm}^{-1}$) : 1576(s), 1537(s), 1505 (s), 1490(s), 1423(s), 1358(s), 1181(m), 1138(s), 476(m), 407(m).

Mass Spectrometry (EI^+) : 707 $[\text{Gd}(\text{thd})_3]^+$ (17%), 651
15 $[\text{Gd}(\text{thd})_2(\text{Bu}'\text{COCHCO})^+$ (23%), 524 $[\text{Gd}(\text{thd})_2]^+$ (18%) and lower mass ions.

Freezing point depression in benzene yields a molecular weight of 1550 ± 63 (calc. 1591).

X-ray structural analysis has confirmed the molecular
20 formula.

33. GADOLINIUM TRIS-THD TETRAGLYME $[\{\text{Gd}(\text{thd})_3\}_2(\text{tetraglyme})]$ - an example of a type II compound.

The $[\text{Gd}(\text{thd})_3]_2$ {prepared via examples 1 and 30} (7.1 g, 5.0 mmole) is dissolved with warming in 70 ml of hexane,
25 tetraglyme (2.22 ml, 10.0 mmole) is added and the solution

- 47 -

stirred at room temperature for 1 hour. The solvent was then removed and the resulting oil left to crystallise.

Yield is 6.4 g 78 %.

Melting point 88-91°C.

5 Microanalysis Found: C, 55.5; H, 8.2. Calcd. $\text{Gd}_2\text{C}_{76}\text{H}_{136}\text{O}_{17}$,
C, 55.8; H, 8.4 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1589(s), 1575(s),
1538(s), 1505 (s), 1359(s), 1181(m), 1139(s), 475(mw),
406(w).

10 Mass Spectrometry (EI^+) : 707 $[\text{Gd}(\text{thd})_3]^+$ (7%), 650
 $[\text{Gd}(\text{thd})_2(\text{Bu}'\text{COCHCO})]^+$ (42%), 524 $[\text{Gd}(\text{thd})_2]^+$ (87%) and lower
mass ions.

X-ray structural analysis, see Figure 7.

34. GADOLINIUM TRIS-THD HEPTAGLYME

15 $[\{\text{Gd}(\text{thd})_3\}_2(\text{heptaglyme})]$ - an example of a type II compound.

The $[\text{Gd}(\text{thd})_3]_2$ {prepared via examples 1 and 30} (7.1 g,
5.0 mmole) is dissolved with warming in 70 ml of hexane,
heptaglyme (3.50 ml, 10.0 mmole) is added and the solution
stirred at room temperature for 1 hour. The solvent was then
20 removed and the resulting oil left to crystallise for 4 hs.
at 20°C.

Yield is 8.0 g 91 %.

Melting point 82-84°C.

Microanalysis Found: C, 55.6; H, 8.4. Calcd. $\text{Gd}_2\text{C}_{82}\text{H}_{148}\text{O}_{20}$,
25 C, 55.7; H, 8.4 %.

- 48 -

Infrared spectrometry (Nujol ν cm^{-1}) : 1575(s), 1538(s), 1505 (s), 1423(s), 1358(s), 1227(ms), 1180(m), 1137(s), 476(w), 405(w).

Mass Spectrometry (EI^+) : 1509 $[\text{Gd}_2(\text{thd})_6(\text{triglyme})]^+$ (1%), 1354 $[\text{Gd}_2(\text{thd})_5(\text{Bu}'\text{COCHCO})]^+$ (5%), $[\text{Gd}_2(\text{thd})_5]^+$ (24%), and lower mass ions.

X-ray structural analysis, see Figure 6.

35. GADOLINIUM TRIS-THD HEXAMETHYLTRIETHYLENETETRAMINE

$[\{\text{Gd}(\text{thd})_3\}_2(\text{hmteta})]$ - an example of a type II compound.

10 The $[\text{Gd}(\text{thd})_3]_2$ {prepared via examples 1 and 30} (7.1 g, 5.0 mmole) is dissolved with warming in 70 ml of hexane, hmteta (2.3 ml, 10.0 mmole) is added and the solution stirred at room temperature for 1 hour. The solvent was then removed and the resulting oil left to crystallise for 4 hs. at
15 20°C.

Yield is 7.0 g 84 %.

Melting point 91-93°C.

Microanalysis Found: C, 57.4; H, 8.9. Calcd.

$\text{Gd}_2\text{C}_{78}\text{H}_{144}\text{O}_{12}\text{N}_4$, C, 57.0; H, 8.8 %.

20 Infrared spectrometry (Nujol ν cm^{-1}) : 1574(s), 1533(s), 1501 (s), 1452(s), 1371(s), 1222(m), 1176(m), 402(w).

Mass Spectrometry (EI^+) : 1643 $[\text{Gd}_2(\text{thd})_6(\text{hmteta})]^+$ (1%), 1354 $[\text{Gd}_2(\text{thd})_5(\text{Bu}'\text{COCHCO})]^+$ (5%), $[\text{Gd}_2(\text{thd})_5]^+$ (24%), and lower mass ions.

- 49 -

Sublimation: Sublimes in excellent yield over the range 85-120°C and 1×10^{-3} torr.

Freezing point depression in benzene yields a molecular weight of 1570 ± 78 (calc. 1624).

5 36. GADOLINIUM TRIS-ACAC DIMETHOXYETHANE

[Gd(acac)₃(dme)] - an example of a type I compound.

The preparation of [Gd(acac)₃(dme)] is similar to the method used for example 3. The quantities used are [Gd(hmdz)₃]_n (6 g, 9.4 mmole), acacH (2.8 g, 28.2 mmole) and
10 monoglyme (1.7 ml, 18.8 mmole). The solution is stirred at room temperature for 1 hour and then stripped to an oil and set aside at 20°C to crystallise.

Yield is 4.3 g, 83 % of colourless air stable crystals.

Melting point shows evidence of dissolving in the glyme
15 126-135°C.

Microanalysis Found: C, 42.1; H, 5.9. Calcd. GdC₁₉H₃₁O₈, C, 41.9; H, 5.7 %.

Infrared spectrometry (Nujol ν cm⁻¹) : 1571(s), 1534(s), 1504 (s), 1450(m), 1351(s), 1226(m), 1135(s), 405(w).

20 Mass Spectrometry (EI⁺) : 544 [Gd(acac)₃(dme)]⁺ (5%), 454 [Gd(acac)₃]⁺ (17%), 355 [Gd(acac)₂]⁺ (16%), and lower mass ions.

37. TERBIUM TRIS-THD TETRAMETHYLETHYLENEDIAMINE

[Tb(thd)₃(tmeda)] - an example of a type I compound.

- 50 -

The first part of the preparation employs a similar method to example 1 to yield $[\text{Tb}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Tb}(\text{thd})_3(\text{H}_2\text{O})]_n$ (10.0 g, 13.8 mmole) is dissolved with warming in 60 ml of hexane, tmeda (3.2 ml, 27.6 mmole) is
5 added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 8.3 g, 72 % of pink air stable crystals.

Melting point 98-100°C.

10 Microanalysis Found: C, 57.0; H, 8.9. Calcd. $\text{TbC}_{39}\text{H}_{73}\text{O}_6\text{N}_2$, C, 56.8; H, 8.9 %.

Freezing point depression in benzene yields a molecular weight of 805±37 (calc. 824).

38. TERBIUM TRIS-THD TRIGLYME $[\{\text{Tb}(\text{thd})_3\}_2(\text{triglyme})]$ -
15 an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield $[\text{Tb}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Tb}(\text{thd})_3(\text{H}_2\text{O})]_n$ (10.0 g, 13.8 mmole) is dissolved with warming in 60 ml of hexane, triglyme (4.9ml, 27.6 mmole)
20 is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 13.3 g, 89 % of pale-pink air stable crystals.

Melting point 86-89°C.

- 51 -

Microanalysis Found: C, 55.3; H, 8.2. Calcd. $Tb_2C_{74}H_{132}O_{16}$,
C, 55.7; H, 8.3 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1609(s),
1589(s), 1574(vs), 1536(s), 1505(s), 1452(m), 1422(m),
5 1388(s), 1359(vs), 1179(m), 1131(s), 474(m), 406(m).

Mass Spectrometry (EI⁺) : 708 $[Tb(thd)_3]^+$ (4%), 653
 $[Tb(thd)_2(Bu'COCHCO)]^+$ (12%), 524 $[Tb(thd)_2]^+$ (9%) and lower
mass ions.

Freezing point depression in benzene yields a molecular
10 weight of 1555 ± 83 (calc. 1594).

39. TERBIUM TRIS-TFA TETRAGLYME

$[Tb(tfa)_3]_2(tetraglyme)_2$ - an example of a type II compound.

The first part of the preparation employs a similar
method to example 1 to yield $[Tb(tfa)_3(H_2O)]_2$.

15 The $[Tb(tfa)_3(H_2O)]_2$ (5.0 g, 6.9 mmole) is suspended in 200
ml of warm hexane, tetraglyme (3.1 ml, 13.8 mmole) is added
and the solution stirred at room temperature for 1 hour. It
is then stripped to an oil and set aside at 20°C to
crystallise.

20 Yield is 4.2 g, 64 % of pale-pink air stable crystals.

Melting point 83-85°C.

Microanalysis Found: C, 33.0; H, 3.4. Calcd.
 $Tb_2C_{40}H_{46}O_{17}F_{18}$, C, 32.9; H, 3.2 %.

- 52 -

Infrared spectrometry (Nujol ν cm^{-1}) : 1583(s), 1571(s), 1532(m), 1504(s), 1357(s), 1280(m), 1226(m), 1182(m), 1137(s), 474(m), 405(w).

Mass Spectrometry (EI^+) : 1083 [$\text{Tb}_2(\text{tfa})_3$] $^+$ (2%), 618
5 [$\text{Tb}(\text{tfa})_3$] $^+$ (9%), and lower mass ions.

40. DYSPROSIUM TRIS-ACAC TETRAGLYME

[$\{\text{Dy}(\text{acac})_3\}_2(\text{tetraglyme})$] - an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield [$\text{Dy}(\text{acac})_3(\text{H}_2\text{O})_2$] $_n$. The
10 [$\text{Dy}(\text{acac})_3(\text{H}_2\text{O})_2$] $_n$ (3.0 g, 6.0 mmole) is suspended in 60 ml of ethanol, tetraglyme (2.7 ml, 12 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 2.35 g, 41 % of pale-yellow air stable
15 crystals.

Melting point dissolves in the parent glyme, with no clear M. Pt.

Microanalysis Found: C, 42.5; H, 5.9. Calcd. $\text{Dy}_2\text{C}_{40}\text{H}_{64}\text{O}_{17}$,
C, 42.1; H, 5.6 %.

20 Infrared spectrometry (Nujol ν cm^{-1}) : 1607(s), 1585(s), 1572(m), 1534(s), 1504(s), 1454(m), 1418(s), 1388(s), 1359(s), 1130(s), 474(m), 404(w).

Freezing point depression in benzene yields a molecular weight of 1115 \pm 42 (calc. 1141).

- 53 -

41. DYSPROSIUM TRIS-THD TRIGLYME

$[\{\text{Dy}(\text{thd})_3\}_2(\text{triglyme})]$ - an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield $[\text{Dy}(\text{thd})_3(\text{H}_2\text{O})]_n$.

5 The $[\text{Dy}(\text{thd})_3(\text{H}_2\text{O})]_n$ (2.5 g, 3.4 mmole) is dissolved with warming in 40 ml of hexane, triglyme (1.2 ml, 6.8 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

10 Yield is 3.2 g, 85 % of pale-pink air stable crystals.
Melting point 85-87°C.

Microanalysis Found: C, 55.7; H, 8.1. Calcd. $\text{Dy}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$,
C, 55.5; H, 8.2 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1609(s), 1589(s),
15 1574(m), 1536(vs), 1504(s), 1452(s), 1422(m), 1388(s),
1359(vs), 1250(m), 1221(s), 1182(s), 1135(s), 404(w).
Freezing point depression in benzene yields a molecular
weight of 1565 \pm 75 (calc. 1601).

Mass Spectrometry (EI⁺) : 708 $[\text{Dy}(\text{thd})_3]^+$ (11%), 653
20 $[\text{Dy}(\text{thd})_2(\text{Bu}'\text{COCHCO})]^+$ (19%), 524 $[\text{Dy}(\text{thd})_2]^+$ (3%) and lower
mass ions.

42. DYSPROSIUM TRIS-THD HEPTAGLYME

$[\{\text{Dy}(\text{thd})_3\}_2(\text{heptaglyme})]$ - an example of a type II compound.

The first part of the preparation employs a similar
25 method to example 1 to yield $[\text{Dy}(\text{thd})_3(\text{H}_2\text{O})]_n$.

- 54 -

The $[\text{Dy}(\text{thd})_3(\text{H}_2\text{O})]_n$ (1.5 g, 2.1 mmole) is dissolved with warming in 20 ml of hexane, heptaglyme (1.46 ml, 4.1 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to
5 crystallise.

Yield is 1.7 g, 76 % of pale-yellow air stable crystals.

Melting point 67-70°C.

Microanalysis Found: C, 55.8; H, 8.4. Calcd. $\text{Dy}_2\text{C}_{82}\text{H}_{148}\text{O}_{20}$,
C, 55.4; H, 8.3 %.

10 Infrared spectrometry (Nujol ν cm^{-1}) : 1574(s), 1536(s),
1504 (vs), 1420(m), 1354(s), 1225(s), 1178(m), 1136(s),
474(w), 403(w).

Mass Spectrometry (EI^+) : 1603 $[\text{Dy}_2(\text{thd})_6(\text{triglyme})]^+$
(0.5%), 1360 $[\text{Dy}_2(\text{thd})_5(\text{Bu}'\text{COCHCO})]^+$ (3%), 1240 $[\text{Dy}_2(\text{thd})_5]^+$
15 (17%), and lower mass ions.

43. HOLMIUM TRIS-THD TRIGLYME $[\{\text{Ho}(\text{thd})_3\}_2(\text{triglyme})]$
- an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield $[\text{Ho}(\text{thd})_3(\text{H}_2\text{O})]_n$.

20 The $[\text{Ho}(\text{thd})_3(\text{H}_2\text{O})]_n$ (2.5 g, 3.4 mmole) is dissolved with warming in 40 ml of hexane, triglyme (1.2 ml, 6.8 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

- 55 -

Yield is 2.9 g, 78 % of pale-yellow air stable crystals.

Melting point 76-78°C.

Microanalysis Found: C, 55.6; H, 8.4. Calcd. $\text{Ho}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$,
C, 55.3; H, 8.2 %.

5 Infrared spectrometry (Nujol ν cm^{-1}) : 1608(s), 1588(s),
1574(m), 1535(vs), 1504(s), 1451(s), 1421(m), 1388(s),
1359(vs), 1252(m), 1220(s), 1180(s), 1134(s), 403(w).

Freezing point depression in benzene yields a molecular
weight of 1550±70 (calc. 1606).

10 44. HOLMIUM TRIS-HFA TETRAGLYME

[{Ho(hfa)₃},(tetraglyme)] - an example of a type II compound.

The preparation of $\text{Ho}(\text{hfa})_3(\text{H}_2\text{O})_n$ is similar to the
method used for example 1. The $[\text{Ho}(\text{hfa})_3(\text{H}_2\text{O})]_n$ (1.5 g, 1.9
mmole) was dissolved with warming in 20 ml of ethanol,
15 tetraglyme (0.85ml, 3.8 mmole) is added and the solution
stirred at room temperature for 1 hour. It is then stripped
to an oil and set aside at 20°C to crystallise.

Yield is 2.1 g 89 %.

Melting point 72-74°C.

20 Microanalysis Found: C, 27.0; H, 1.9. Calcd.

$\text{Ho}_2\text{C}_{40}\text{H}_{28}\text{O}_{17}\text{F}_{36}$, C, 26.8; H, 1.57 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1572(s), 1531(s),
1502 (m), 1450(s), 1370(s), 1222(m), 1175(m), 1134(s),
403(w).

- 56 -

Mass Spectrometry (EI^+) : 1365 $[Ho_2(hfa)_3]^+$ (9%), 786 $[Ho(hfa)_3]^+$ (24%), and lower mass ions due to hfa dissociation.

Freezing point depression in benzene yields a molecular weight of 1735 ± 83 (calc. 1794).

45. HOLMIUM TRIS-TFA HEXAMETHYLTRIETHYLENETETRAAMINE
 $[Ho(tfa)_3]_2(hmteta)$ - an example of a type II compound.

The preparation of $Ho(tfa)_3(H_2O)_n$ is similar to the method used for example 1. The $[Ho(tfa)_3(H_2O)]_n$ (2.5 g, 3.9 mmole) was dissolved with warming in 30 ml of ethanol, hmteta (1.75 g, 7.8 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 3.2 g, 74 % of pale-yellow air stable crystals.

Melting point 88-92°.

Microanalysis Found: C, 34.4; H, 4.1. Calcd.

$Ho_2C_{42}H_{54}O_{12}F_{18}N_4$, C, 34.1; H, 3.7 %.

Mass Spectrometry (EI^+) : 1095 $[Ho_2(tfa)_3]^+$ (5%), 624 $[Ho(tfa)_3]^+$ (64%) and lower mass ions containing tfa fragments.

46. ERBIUM TRIS-THD DIMETHOXYETHANE $[Er(thd)_3(dme)]$ - an example of a type I compound.

The first part of the preparation employs a similar method to example 1 to yield $[Er(thd)_3(H_2O)]_n$.

- 57 -

The $[\text{Er}(\text{thd})_3(\text{H}_2\text{O})]_n$ (6.0 g, 8.2 mmole) is dissolved with warming in 40 ml of hexane, diglyme (2.2 ml, 16.4 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to
5 crystallise.

Yield is 6.7 g, 81% of pink air stable crystals.

Melting point : 94-96°C.

Microanalysis Found: C, 55.0; H, 8.8. Calcd. $\text{ErC}_{37}\text{H}_{49}\text{O}_8$,
C, 54.9; H, 8.5 %.

10 Freezing point depression in benzene yields a molecular weight of 780 ± 32 (calc. 808).

47. ERBIUM TRIS-THD DIGLYME $[\text{Er}(\text{thd})_3(\text{diglyme})]_2$ - an example of a type III compound.

The first part of the preparation employs a similar
15 method to example 1 to yield $[\text{Er}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Er}(\text{thd})_3(\text{H}_2\text{O})]_n$ (4.25 g, 5.8 mmole) is dissolved with warming in 40 ml of hexane, diglyme (1.56 ml, 11.6 mmole) is added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to
20 crystallise.

Yield is 4.17 g, 83 % of pink air stable crystals.

Melting point 72-74°C.

Microanalysis Found: C, 28.1; H, 4.6. Calcd. $\text{ErC}_{39}\text{H}_{71}\text{O}_9$,
C, 27.5; H, 4.2 %.

- 58 -

Infrared spectrometry (Nujol ν cm^{-1}) : 1576(vs),
1534(s), 1504(vs), 1455(vs), 1376(s), 1180(m), 1137(s),
473(m), 402(w).

Mass Spectrometry (EI^+) : 717 $[\text{Er}(\text{thd})_3]^+$ (37%), 656
5 $[\text{Er}(\text{thd})_2(\text{Bu}'\text{COCHCO})]^+$ (26%), 534 $[\text{Er}(\text{thd})_2]^+$ (100%) and lower
mass ions.

48. ERBIUM TRIS-THD TRIGLYME $[\{\text{Er}(\text{thd})_3\}_2(\text{triglyme})]$ -
an example of a type II compound.

The first part of the preparation employs a similar
10 method to example 1 to yield $[\text{Er}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Er}(\text{thd})_3(\text{H}_2\text{O})]_n$ (20 g, 27.2 mmole) is dissolved with
warming in 40 ml of hexane, triglyme (9.6 ml, 54.4 mmole) is
added and the solution stirred at room temperature for 1
hour. It is then stripped to an oil and set aside at 20°C to
15 crystallise.

Yield is 17.4 g, 70 % of pink air stable crystals.

Melting point 80-82°C.

Microanalysis Found: C, 55.3; H, 8.3. Calcd. $\text{Er}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$,
C, 55.1; H, 8.2 %.

20 Infrared spectrometry (Nujol ν cm^{-1}) : 1608(s), 1587(s),
1573(m), 1535(vs), 1505(s), 1453(s), 1422(m), 1386(s),
1358(vs), 1251(m), 1220(s), 1180(s), 1135(s), 405(w).

Freezing point depression in benzene yields a molecular
weight of 1570 ± 72 (calc. 1610).

- 59 -

Mass Spectrometry (EI⁺) : 711 [Er(thd)₃]⁺ (11%), 656 [Er(thd)₂(Bu'COCHCO)]⁺ (19%), 527 [Er(thd)₂]⁺ (3%) and lower mass ions.

49. THULIUM TRIS-THD TRIGLYME [{Tm(thd)₃]₂(triglyme)]

5 - an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield [Tm(thd)₃(H₂O)]_n.

The [Tm(thd)₃(H₂O)]_n (1.07 g, 1.45 mmole) is dissolved with warming in 20 ml of hexane, triglyme (0.6 ml, 2.9 mmole) is
10 added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 0.9 g, 77 % of pale-green air stable crystals.

Melting point 65-68°C.

15 Microanalysis Found: C, 55.1; H, 8.3. Calcd. Tm₂C₇₄H₁₃₂O₁₆, C, 55.0; H, 8.2 %.

Infrared spectrometry (Nujol ν cm⁻¹) : 1608(s), 1590(s), 1577(vs), 1538(vs), 1506(s), 1422(vs), 1359(v), 1286(w), 1246(w), 1226(m), 1180(m), 1140(sm), 404(w).

20 **50. THULIUM TRIS-THD TETRAGLYME**

[{Tm(thd)₃]₂(tetraglyme)] - an example of a type II compound.

The first part of the preparation employs a similar method to example 1 to yield [Tm(thd)₃(H₂O)]_n. The

[Tm(thd)₃(H₂O)]_n (1.07 g, 1.45 mmole) is dissolved with
25 warming in 30 ml of hexane, tetraglyme (0.65 ml, 2.90 mmole)

- 60 -

is added and the solution stirred at room temperature for 1 hour. The solvent was then removed and the resulting oil left to crystallise.

Yield is 1.10 g 63 % of yellow-green air-stable
5 crystals.

Melting point 71-73°C.

Microanalysis Found: C, 55.4; H, 8.2. Calcd. $\text{Tm}_2\text{C}_{76}\text{H}_{136}\text{O}_{17}$,
C, 55.0; H, 8.2 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1589(s), 1575(s),
10 1538(s), 1505 (s), 1359(s), 1181(m), 1139(s), 475(mw),
406(w).

Freezing point depression in benzene yields a molecular
weight of 1590 ± 84 (calc. 1658).

Mass Spectrometry (EI^+) : 719 $[\text{Tm}(\text{thd})_3]^+$ (7%), 662
15 $[\text{Tm}(\text{thd})_2(\text{Bu}'\text{COCHCO})]^+$ (42%), 536 $[\text{Tm}(\text{thd})_2]^+$ (87%) and lower
mass ions.

51. THULIUM TRIS-ACAC HEPTAGLYME

$[\{\text{Tm}(\text{acac})_3\}_2(\text{heptaglyme})]$ - an example of a type II compound.

The preparation of $[\text{Tm}(\text{acac})_3]_2$ is similar to the method
20 used for example 3. The quantities used are $[\text{Tm}(\text{hmdz})_3]_2$ (2
g, 3.1 mmole), acacH (0.93 ml, 9.3 mmole) and heptaglyme
(2.2 ml, 6.2 mmole). The solution is stirred at room
temperature for 1 hour and then stripped to an oil and set
aside at 20°C to crystallise.

- 61 -

Yield is 2.5 g, 62% of yellow air stable crystals.

Melting point : 83-85°C.

Microanalysis Found: C, 43.2; H, 6.0. Calcd. $\text{Tm}_2\text{C}_{46}\text{H}_{76}\text{O}_{20}$,
C, 42.9; H, 5.9 %.

5 Mass Spectrometry (EI^+) : 1286 [$\text{Tm}_2(\text{acac})_6(\text{heptaglyme})$] $^+$
(0.3%), 833 [$\text{Tm}_2(\text{acac})_5$] $^+$ (42%), 466 [$\text{Tm}(\text{acac})_3$] $^+$ (24%) and
lower mass ions.

52. YTTERBIUM TRIS- Ph_2ACAC

PENTAMETHYLDIETHYLENETRIAMINE [$\text{Yb}(\text{Ph}_2\text{acac})_3(\text{pmdeta})$] - an
10 example of a type I compound.

The first part of the preparation employs a similar
method to example 3, to yield [$\text{Yb}(\text{Ph}_2\text{acac})_3$] $_n$. The
[$\text{Yb}(\text{acac})_3$] $_n$ (2.0 g, 4.25 mmole) is suspended in 50 ml of
chloroform, pmdeta (1.5 ml, 8.5 mmole) is added and the
15 solution stirred at room temperature for 1 hour. It is then
stripped to an oil and set aside at 20°C to crystallise.

Yield is 3.2 g, 92% of colourless air stable crystals.

Melting point 126-130°C.

Microanalysis Found: C, 64.2; H, 5.8. Calcd. $\text{YbC}_{34}\text{H}_{56}\text{O}_6\text{N}_3$,
20 C, 63.8; H, 5.5 %.

Mass Spectrometry (EI^+): 1016 [$\text{Yb}(\text{Ph}_2\text{acac})_3(\text{pmdeta})$] $^+$
(19%), 842 [$\text{Yb}(\text{Ph}_2\text{acac})_3$] $^+$ (7%) and lower mass species.

53. YTTERBIUM TRIS-THD DIGLYME [$\text{Yb}(\text{thd})_3(\text{diglyme})$] -
an example of a type I compound.

- 62 -

The first part of the preparation employs a similar method to example 1 to yield $[\text{Yb}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Yb}(\text{thd})_3(\text{H}_2\text{O})]_n$ (0.8 g, 1.22 mmole) is dissolved with warming in 10 ml of hexane, diglyme (0.34 ml, 2.5 mmole) is
5 added and the solution stirred at room temperature for 1 hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 0.74 g, 76 % of colourless air stable crystals.

Melting point 72-74°C.

10 Microanalysis Found: C, 55.1; H, 8.6. Calcd. $\text{YbC}_{39}\text{H}_{71}\text{O}_9$, C, 54.7; H, 8.3 %.

Infrared spectrometry (Nujol ν cm^{-1}) : 1576(vs), 1534(s), 1504(vs), 1455(vs), 1376(s), 1180(m), 1137(s), 473(m), 402(w).

15 Mass Spectrometry (EI^+) : 717 $[\text{Er}(\text{thd})_3]^+$ (37%), 656 $[\text{Er}(\text{thd})_2(\text{Bu}'\text{COCHCO})]^+$ (26%), 534 $[\text{Er}(\text{thd})_2]^+$ (100%) and lower mass ions.

54. YTTERBIUM TRIS-THD TRIGLYME

$[\{\text{Yb}(\text{thd})_3\}_2(\text{triglyme})]$ - an example of a type II compound.

20 The first part of the preparation employs a similar method to example 1 to yield $[\text{Yb}(\text{thd})_3(\text{H}_2\text{O})]_n$.

The $[\text{Yb}(\text{thd})_3(\text{H}_2\text{O})]_n$ (0.8 g, 1.22 mmole) is dissolved with warming in 20 ml of hexane, diglyme (0.34 ml, 2.5 mmole) is added and the solution stirred at room temperature for 1

- 63 -

hour. It is then stripped to an oil and set aside at 20°C to crystallise.

Yield is 0.73 g, 66 % of air stable crystals.

Melting point 68-70°C.

5 Microanalysis Found: C, 54.8; H, 8.3. Calcd. $\text{Yb}_2\text{C}_{74}\text{H}_{132}\text{O}_{16}$,
C, 54.7; H, 8.1 %.


Infrared spectrometry (Nujol ν cm^{-1}) : 1607(s), 1590(s),
1577(vs), 1538(vs), 1506(s), 1423(vs), 1359(vs), 1288(w),
1245(w), 1222(m), 1181(m), 1136(s), 404(w).

10 Freezing point depression in benzene yields a molecular
weight of 1670 ± 72 (calc. 1712).

- 64 -

CLAIMS


1. Rare earth compounds of formula



where M represents one or more metals chosen from the rare
 5 earth metals and yttrium, L is a bidentate ligand, A is a
 polyether, polyamine or polyether-amine, and x and y are each
 1 or 2 but are not both 2.

2. A compound according to claim 1 wherein L contains
 a ligand group of formula


10



3. A compound according to claim 1 wherein L is a β -
 diketone ligand.


- 15 4. A compound according to claim 1 wherein the ligand
 L is derived from one or more of acetylacetone,
 tetramethylheptanedione, trifluoroacetylacetone,
 hexafluoroacetylacetone, and 1,5-diphenylpentanedione.

5. A compound according to any one of claims 1 to 4
 20 wherein A is derived from a polyether of formula:



- wherein R^1 , R^2 and R^3 are each hydrogen or alkyl of 1 to 4
 25 carbon atoms, and n is from 1 to 10, and/or from a polyamine
 of formula:

- 65 -



wherein R^1 , R^2 and R^3 and n are as hereinbefore defined.

5 6. A compound according to claim 5 wherein A is derived from a said polyether wherein R^1 and R^2 are each alkyl of 1 to 4 carbon atoms, R^3 is hydrogen, and n is an integer from 1 to 7.

7. A compound according to claim 5 wherein A is
10 derived from monoglyme, diglyme, triglyme, tetraglyme, and/or heptaglyme.

8. A compound according to claim 5 wherein A is derived from a said polyamine wherein R^1 and R^2 are each alkyl of 1 to 4 carbon atoms, R^3 is hydrogen, and n is an integer
15 from 1 to 3.

9. A compound according to claim 5 wherein A is derived from tmeda, pmdeta, and/or hmteta.


10. A compound according to claim 1 where L is derived from acetylacetone, tetramethylheptanedione, or
20 diphenylacetylacetone, A is derived from monoglyme, tetraglyme, tmeda, or pmdeta, $x = 1$ and $y = 1$.

11. A compound according to claim 1 wherein L is derived from acetylacetone, tetramethylheptanedione, trifluoroacetylacetone, hexafluoroacetylacetone, or
25 diphenylacetylacetone, A is derived from triglyme, tetraglyme, heptaglyme, or hmteta, $x = 2$ and $y = 1$.

- 66 -

12. A compound according to claim 1 wherein L is derived from tetramethylheptanedione or hexafluoroacetylacetone, A is derived from diglyme, $x = 1$ and $y = 2$.
- 5 13. A compound according to any one of claims 1 to 12 wherein M is yttrium, a combination of yttrium with europium or terbium, lanthanum, a combination of lanthanum and thulium, cerium, praseodymium, neodymium, samarium, europium, gadolinium, terbium, dysprosium, holmium, erbium, thulium, or
10 ytterbium.
14. Process for the preparation of a rare earth compound as claimed in any one of claims 1 to 13 which comprises reacting a rare earth compound of formula:
- $$M(NR^4)_3 \text{ or } M(OR^5)_3$$
- 15 where M represents one or more metals chosen from the rare earth metals and yttrium, R^4 is alkyl of 1 to 4 carbon atoms or trimethylsilyl, and R^5 is alkyl of 1 to 4 carbon atoms optionally substituted by alkoxy of 1 to 4 carbon atoms, with a bidentate ligand LH and a polyether, polyamine, or
20 polyether-amine A.
15. Process according to claim 14 wherein the process is carried out in a hydrocarbon solvent.
16. Process for the preparation of a rare earth compound as claimed in any one of claims 1 to 13 which
25 comprises reacting a rare earth compound of formula:

- 67 -



where M represents one or more metals chosen from the rare earth metals and yttrium and Z represents an anion with an alkali metal derivative of the bidentate ligand LH and a
5 polyether, polyamine, or polyether-amine A.

17. Process according to claim 16 wherein Z is a halide, carboxylate, sulphate, or nitrate anion and the reaction is conducted in an alcohol solvent.

18. Process for the preparation of a rare earth
10 compound as claimed in any one of claims 1 to 13 which comprises reacting a rare earth oxide, hydroxide or carbonate with the bidentate ligand LH and a polyether, polyamine or polyether-amine A.

19. Process according to claim 18 wherein the reaction
15 is conducted in a hydrocarbon solvent using the metal oxide.

20. A compound according to any one of claims 1 to 13 having a molecular weight less than 1000 per metal atom.

21. A solution in an organic solvent of a compound according to any one of claims 1 to 13 or 20.

20 22. Use of a compound according to any one of claims 1 to 13 or 20 in a chemical vapour deposition process, in vapour phase catalysis, or in a sol-gel process.

23. A fuel having dissolved or dispersed therein a compound according to any one of claims 1 to 13 or 20.

25 24. A fuel according to claim 23 for an internal combustion engine.

- 68 -

25. A hydrocarbon fuel according to claim 23 for a compression ignition engine.

26. A hydrocarbon fuel according to claim 23 wherein the concentration of rare earth metal is 10 to 500 ppm,
5 preferably 50 to 200 ppm by weight.

27. A solution according to claim 21 wherein the concentration of rare earth metal is at least 10%, preferably at least 15%, by weight.

28. A compound according to any one of claims 1 to 13
10 having a rare earth metal content of at least 10%, preferably at least 15%, by weight.

1/12

Fig.1.






Fig.2.



SUBSTITUTE SHEET

2/12

Fig.3.



SUBSTITUTE SHEET

3/12

Fig.4.






Fig.6.



4/12

Fig.5.



SUBSTITUTE SHEET

5/12

Fig.7.





Fig.8.



SUBSTITUTE SHEET

6/12

Fig.9a





Fig.9b



SUBSTITUTE SHEET

7/12

Fig.10a





Fig.10b



SUBSTITUTE SHEET

8/12

Fig.11a

SMPL ID : Eu (thd)₃(triglyme)
STA 1500H RUN ID : DJO 165 GAS 1 : N2 30%
SIZE : 9.694 MG UNIT No : 1





Fig.11b

SMPL ID : Eu (thd)₃(triglyme)
STA 1500H RUN ID : DJO 165 GAS 1 : N2 30%
SIZE : 9.694 MG UNIT No : 1



SUBSTITUTE SHEET

9/12

Fig.12a

SMPL ID : YEu (thd)₆ (triglyme)
STA 1500H RUN ID : DJO 194 GAS 1 : N2 30%
SIZE : 13.117 MG UNIT No : 1





Fig.12b

SMPL ID : YEu (thd)₆ (triglyme)
STA 1500H RUN ID : DJO 194 GAS 1 : N2 30%
SIZE : 13.117 MG UNIT No : 1



SUBSTITUTE SHEET

10/12

Fig.13a





Fig.13b



SUBSTITUTE SHEET

11/12

Fig.14a





Fig.14b



12/12

Fig.15a





Fig.15b



SUBSTITUTE SHEET

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C07F5/00 C23C16/18 C10L1/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C07F C23C C10L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	TETRAHEDRON LETTERS no. 17, 1973 pages 1467 - 1470 GROTENS, A.M. ET AL. 'LANTHANIDE INDUCED CONTACT SHIFTS IN POLYGLYCOLDIMETHYLEETHERS, IV CHEMICAL EXCHANGE' see the whole document ---	1-13
A	WO,A,89 07666 (NORTHWESTERN UNIVERSITY) 24 August 1989 see the whole document --- -/--	1-22

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- 'A' document defining the general state of the art which is not considered to be of particular relevance
- 'E' earlier document but published on or after the international filing date
- 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- 'O' document referring to an oral disclosure, use, exhibition or other means
- 'P' document published prior to the international filing date but later than the priority date claimed

'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

'&' document member of the same patent family

Date of the actual completion of the international search

3 March 1994

Date of mailing of the international search report

15. 03. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Rinkel, L

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 94/00120

C/(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 112, no. 24, 11 June 1990, Columbus, Ohio, US; abstract no. 228202j, NIGREY, P.J. 'THIN-FILM SUPERCONDUCTOR MANUFACTURE' page 771 ; see abstract & US-Published Patent Application-146640 published 1-11-1989, application 21-1-1988 (Nigrey, P.J.; United States Dept. of Energy) NTIS Order No. PAT-APPL-7-146640 ---	1,22
A	CHEMICAL ABSTRACTS, vol. 84, no. 12, 22 March 1976, Columbus, Ohio, US; abstract no. 76591y, TISCHER, R.L. ET AL. 'NEW RARE EARTH ANTIKNOCK ADDITIVES THAT ARE POTENTIAL SUBSTITUTES FOR TETRAETHYL LEAD' page 151 ; see abstract & U.S. Aerosp. Res. Lab., (Rep.) 1974 ARL TR 74-0170 ---	1,23-27
A	CHEMICAL ABSTRACTS, vol. 108, no. 20, 16 May 1988, Columbus, Ohio, US; abstract no. 178960z, AIZENBERG, M.I. ET AL. 'SYNTHESIS AND THERMOCHROMATOGRAPHIC INVESTIGATION OF VOLATILE ACETYLACETONATES OF AMERICIUM AND LANTHANIDS' page 790 ; see abstract & RADIOKHIMIYA vol. 29, no. 6 , 1987 pages 722 - 725 ---	1,22
A	US,A,3 254 103 (MELBY, L.R. ET AL.) 31 May 1966 see the whole document ---	1
X	JOURNAL OF THE CHEMICAL SOCIETY DALTON TRANSACTIONS no. 15 , 1993 pages 2379 - 2386 DRAKE, S.R. ET AL. 'LANTHANIDE .BETA.-DIKETONATE GLYME COMPLEXES EXHIBITING UNUSUAL COORDINATION MODES' see the whole document -----	1-28

Information on patent family members

International Application No

PCT/GB 94/00120

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8907666	24-08-89	US-A- 5185317	09-02-93
US-A-3254103		NONE	